

m41.o04


Very strong ferromagnetic interaction in a new asymmetrical binuclear μ -methoxy-bridged Mn(III) complex

Chahrazed Beghidja^a, Guillaume Rogez^b, Jens Kortus^b, Richard Welter^a

DECOMET lab. CNRS-ULP 7177, Université Louis Pasteur Strasbourg I, F-67070 Strasbourg cedex, France and I.P.C.M.S., UMR 7504 CNRS-ULP, Groupe des Matériaux Inorganiques, Strasbourg cedex 2, France. E-mail: welter@chimie.u-strabg.fr

Keywords: single molecule magnet, manganese complex, hydrogen bond

Manganese complexes can act as paramagnetic building blocks for Single Molecule Magnets (SMM) and also for multidimensional expanded structures.[1] The magnetic behavior of a variety of such compounds has been explored during the last decades with the aim of designing SMM or Single Chain Magnets.[2,3] The choice of binuclear transition metal building blocks with different exchange coupling patterns creates a number of exciting possibilities in this area.[4] In this communication, we present the preparation, crystal structure analysis and a detailed magnetic study of exchange interaction between manganese centers of the dinuclear Mn(III)₂(μ -OMe)₂(HL)₄*.[5] The new binuclear Mn(III) complex described here presents one of the strongest intramolecular ferromagnetic interaction ($J=19.7 \text{ cm}^{-1}$). This strong interaction is supported by DFT calculations which also confirm the negative sign of the $D_{S=4}$ parameter. Such binuclear complexes with very strong ferromagnetic interaction and axial magnetic anisotropy are excellent candidates to be incorporated into polymeric and/or supramolecular networks that could present interesting magnetic properties, if one achieves correctly designed interactions.[2]



ORTEP view of the new binuclear complex (left) showing specific intramolecular hydrogen bonds. Partial view of the molecular core (right) with an indication of the relative orientation of Jahn-Teller elongated (d_{z^2}) axes around both Mn(III) atoms.

* $H_2L=2$ -salicyloylhydrazono-1,3-dithiolane.

- [1] Sailaja, S.; Rajender Reddy, K.; Rajasekharan, M. V.; Hureau, C.; RiviÈre, E.; Cano J., Girerd J.-J. *Inorg. Chem* 2003, 42, 180.
 [2] Ferbinteanu, M.; Miyasaka, H.; Wernsdorfer, W.; Nakata, K.; Sugiura, K.-i.; Yamashita, M.; Coulon, C.; ClÈrac, R. *J. Am. Chem. Soc.* 2005, 127, 3090.
 [3] Gatteschi, D.; Sessoli, R. *Angew. Chem. Int. Ed.* 2003, 42, 3
 [4] Viau, G.; Lombardi, M. G.; De Munno, G.; Julve, M.; Lloret, F.; Faus, J.; Caneschi, A.; Clemente-Juan, J. M. *Chem. Commun.* 1997, 1195.
 [5] Beghidja, C.; Rogez, G.; Kortus, J.; Wesolek, M.; Welter, R.; *J. Am. Chem. Soc.* 2006, in press.

m41.o05

New Compounds of L-Alanine with Inorganic Materials

Ekkehart Tillmanns^a, Michel Fleck^a, Ladislav Bohaty^b

^a Institut f. Mineralogie und Kristallographie, Univ. Wien, Althanstr. 14, A-1090 Vienna, Austria ^b Institut für Kristallographie, Universität zu Köln, Zùlpicher Str. 49b, D-50674 Cologne, Germany

Keywords: alanine, crystal structure, amino-acid coordination compounds

We have investigated materials containing alanine and inorganic compounds. Alanine - as all amino acids - is amphoteric, it can act as a cation, as an anion or as a zwitter-ion, i.e., an overall neutral group. Consequently, alanine can combine with anions, cations or overall neutral chemical constituents. Thus, the existence of a large number of compounds of alanine with inorganic materials is conceivable.


A search of the crystallographic data banks (i.e., CSD, PC-PDF) revealed over 200 alanine compounds. However, in most of these substances alanine is combined with other organic molecules. Only 48 compounds of alanine and inorganic materials were found, e.g., Co^{III} L-Alaninate₃·H₂O [1].

We attempted the syntheses of several new members of this group. Although racemic alanine compounds can form non-centrosymmetrical crystals (as it is the case for DL-Alanin itself [2], as well as for the non-chiral amino acid glycine and its salts, e.g. [3]), most of these compounds are centro-symmetrical. Thus, we have used L-alanine exclusively in order to ensure non-centrosymmetry. Recently, we have found three new species, the crystal structures of which are discussed in the presentation. Crystal data (in Å and °):

Alanine alaninium triiodide, s.g. $P2_12_12_1$
 $a = 8.366(2)$, $b = 8.912(2)$, $c = 41.889(8)$

Alanine SrCl₂β3H₂O, s.g. $P2_1$
 $a = 8.540(2)$, $b = 7.167(1)$, $c = 8.769(2)$, $\beta = 95.02(3)$

Alanine NH₄ Zn Cl₃, s.g. $P2_1$ (see figure below)
 $a = 7.944(2)$, $b = 7.567(2)$, $c = 8.903(2)$, $\beta = 109.65(3)$



Crystal structure of Alanine NH₄ Zn Cl₃. Note the polarity of the structure (necessary because of the alanine molecule) is expressed also by the ammonium ions.

- [1] R.Herak, B.Prelesnik, I.Krstanovic (1978) *Acta Cryst.* B34, 91-95.
 [2] M.Subha Nandhini, R.V.Krishnakumar, S.Natarajan (2001), *Acta Cryst.* C57, 614-615.
 [3] M. Fleck, L.Bohaty (2004) *Acta Cryst.* C60 m291-m295.