

and 800 μm capillaries, and counting-time 2000 and 400 seconds/ step respectively. The results of this research will be used in routine forensic investigations in the Prague Institute of Criminalistics.

Keywords: X-ray diffraction; microdiffraction; forensic science

FA5-MS01-P16

Preferred Orientation and the Structure Analysis Of Polycrystalline Materials. Jürgen Grässlin^a, Lynne B. McCusker^a, Christian Baerlocher^a, Fabia Gozzo^b, Bernd Schmitt^b. ^aLaboratory of Crystallography, ETH Zurich, CH-8093 Zurich, Switzerland. ^bSwiss Light Source, PSI, CH-5232 Villigen, Switzerland.
E-mail: juergen.graesslin@mat.ethz.ch

If the crystallites in a polycrystalline sample are oriented, the intensity of a reflection will vary as a function of the orientation of the sample in the X-ray beam. This means that even if two reflections overlap in a conventional powder diffraction pattern (i.e. have the same d -value), their intensities are likely to vary differently as a function of sample orientation, so their individual intensities can be deduced if data are collected at different sample orientations. It has been shown that this principle can indeed be exploited to obtain more single-crystal-like data from a polycrystalline material [1]. Although the initial study was performed in reflection mode, it was soon realized that a transmission geometry offered several advantages and the experiment was adapted accordingly. In particular, the problem of sample homogeneity was eliminated (the sample is bathed in the X-ray beam), the severe correction of the data for the sample tilt was no longer necessary, and less synchrotron beamtime was required. To start with, a 2-dimensional image plate detector was used, but the resolution of the diffraction patterns, both in d_{min} (2θ range) and in peak width proved to be a limitation [2]. To overcome this, the experiment was changed once again to accommodate the 1-dimensional Mythen I Si-microstrip detector that was available on the Materials Science Beamline at SLS [3,4]. Now, a new version of this detector, Mythen II, has become available, and further optimization of the experiment can be undertaken. The detector now has a 2θ range of 120° (vs. 60°), has a much larger dynamic range, and is not plagued by random dead and hot channels. Consequently, a different, more efficient, data collection strategy can be employed. Improvements in the data analysis software *Maud* [5] have also made it possible to reduce the data collection time. Constant 5° steps in the sample rotation (ϕ) and tilt (χ) angles are no longer required, so the number of sample orientations to be measured can be reduced from 1368 to 302 without sacrificing information content. The first measurements with the new detector and the new data collection strategy have now been performed. Textured samples of phlogopite mica and the aluminophosphate $\text{AlPO}_4\text{-17}$ (ERI framework type), with known crystal structures, and of a niobium silicate with an unknown structure have been measured. Preliminary analysis of these data show that sensible orientation distribution functions can be derived, and the

full intensity extractions are in progress. The crystal system of the niobium silicate was ambiguous because unit cells in several different crystal systems (hexagonal, orthorhombic, monoclinic) were possible. The texture analysis has now shown that only the orthorhombic unit cell is consistent with the measured pole figures.

[1] Baerlocher, Ch.; McCusker, L.B.; Prokic, S.; Wessels, T. *Z. Kristallogr.* 219, 803-812, **2004**. [2] Prokic, S. *Ph.D. Thesis*, University of Zürich, Switzerland, **2004**. [3] Massüger, L. *Ph.D. Thesis*, ETH Zürich, Switzerland, **2007**. [4] Schmitt, B. et al. *Nucl. Inst. Meth. A* 501, 267-272, **2003**. [5] Lutterotti, L.; Matthies, S.; Wenk, H.-R.; *ICOTOM-12*, 1, 1599, **1999**.

Keywords: preferred orientation; structure determination; X-ray powder diffraction

FA5-MS01-P17

Effects of the Ferroelectric Domain Structure of PZT Ceramics on Powder Diffraction. Kristin A. Schoenau^a, Michael Knapp^b, Matteo Leoni^c, Hartmut Fuess^a. ^aMaterials Science, Darmstadt University of Technology, Germany. ^bCELLS, Barcelona, Spain. ^cDept. Materials Engineering and Industrial Technologies, University of Trento, Italy.
E-mail: kristin@cantab.net

Ferroelectric lead zirconate titanate solid solutions, $\text{PbZr}_{1-x}\text{Ti}_x\text{O}_3$ (PZT), are frequently used in industrial applications exploiting the reaction of both the lattice and the domain structure to an applied electric field. Diffraction is a powerful and necessary tool to be able to understand materials reaction and to separate these two effects through analyzing intensity changes and shifts in peak position under electric field.

Highest strain is found for compositions at the morphotropic phase boundary (MPB) between the tetragonal and rhombohedral phase field. Discussions on its origin involved a coexistence of tetragonal and rhombohedral structures as well as the existence of a monoclinic phase [1]. Recent studies using high-resolution synchrotron x-ray powder diffraction in combination with TEM and EPR at ambient temperature [2, 3] were able to correlate XRD observation with a nanodomain structure. Theoretical approaches using Martensitic theory describe these observations with strong coherence effects between ordered nanodomains in diffraction experiments [4].

In XRPD anisotropic peak broadening effects and asymmetries in line shape for distinct hkl are already observed for single phase tetragonal material with a large domain size. But so far the asymmetry and intensity observed in between split reflection pairs have been attributed to diffuse scattering from strained domain walls [5], which is not in line with TEM observations [6].

We therefore analyze diffraction data of single phase tetragonal and rhombohedral PZT in the vicinity of the MPB recorded in transmission mode at the beamline B2, Hasylab, Hamburg Germany, using Rietveld refinement and size-strain analysis to be able to determine a sound basis for analysis of diffraction data of morphotropic PZT samples.

[1] Glazer, A. M.; Thomas, P.A.; Baba-Kishi, K. Z.; Pang, G. K.

H.; Tai, C. W.; *Phys. Rev. B* 70, 184123, **2004**. [2] Schmitt, L.A., Schönau, K.A.; Theissmann, R.; Fuess, H.; Kungl, H.; Hoffmann, M.J.; *J. Appl. Phys.* 101, 074107, **2007**. [3] Schönau, K.A.; Schmitt, L.A.; Knapp, M.; Fuess, H.; Eichel, R.-A.; Kungl, H.; Hoffmann, M.J. *Phys Rev B*, **2007**, 75(14) in press. [4] Wang, Y.U. *Phys. Rev. B* 76 024108, **2007**. [5] Boysen, H.; *Z. Kristallogr.* 220(8), 726, **2005**. [6] Stemmer, S., Streiffer, S. K., Ernst, F., Rühle, M., *Philos. Mag.* A 71, 713, **1995**.

Keywords: ferroelectric oxides; synchrotron x-ray powder diffraction; size-strain

FA5-MS01-P18

Structural Phase Transitions in Nanoscaled Systems with Jahn-Teller Ions. Sophia Petrova^c, Eugenia Vykhodets^d, Robert Zakharov^c, Mikhail Ivanov^b, Nikolai Tkachev^a, Anatolii Fishman^c. ^a*Institute of High-Temperature Electrochemistry UD RAS.* ^b*Institute of Metallophysics NAS of Ukraine.* ^c*Institute of Metallurgy UD RAS.* ^d*Urals' State Technical University (USTU-UPI).*

E-mail: danaus@mil.ru

Specific features of the structural phase transitions of the first order were investigated in nanosized crystals with Jahn-Teller (JT) ions. As an example the phase transitions of martensite type, with changes in symmetry from a cubic (S) to a tetragonal (H) one, have been considered. It was shown the temperature and the latent heat of the transition decrease significantly for the nanoscaled grains. A possibility of multi-phase state with a coexistence of low-symmetry (H) and high-symmetry (S) JT-phases was predicted for the nanocrystalline materials [1] and proved for the nanoscaled Mn-O system (figure). With a certain ratio among parameters of cooperative interactions and random crystal fields at JT ions the structural phase transition can be reduced or suppressed totally. To explain the results the Kanamori model taking into account the size of nanocrystallites, the distribution of cations over non-equivalent crystallographic sublattices as well as the presence of random crystal fields in such systems was used. Figure. Temperature dependence of crystal lattice parameters and a subsequence of phase transitions during heat treatment of the course-grained (closed marks) and nanoscaled (open marks) oxide Mn₂O₃.

[1] Vykhodets E.V., Zakharov R.G., Ivanov M.A., Petrova S.A., Tkachev N.K., Fishman A.Ya., *Materials Science*, **2008**, 138, 53.

Keywords: structural phase transitions; X-ray high-temperature powder diffraction; nanocrystalline materials

FA5-MS01-P19


Structure Determination on Asthmatic Drugs by Synchrotron Powder Diffraction. Jey-Jau Lee^a, S. Thamotharan^b, J. Jeyakanthan^a, R. Bansal^c, R. Yadav^c. ^a*National Synchrotron Radiation Research Center, Taiwan.R.O.C.* ^b*Institute of Bioinformatics and Structural Biology, Department of Life science,*

National Tsing Hua University, Taiwan.R.O.C. ^c*University Institute of Pharmaceutical Sciences, Panjab University, India.*

E-mail: jjlee@nsrrc.org.tw

Asthma is a popular disease nowadays. There are many factors which are responsible for inducing symptoms of asthma. Many classes of drugs namely bronchodilators and anti-inflammatory agents have resulted in substantial improvement in survival and quality of life of asthmatic patients. Here we aim to search for a new chemical entity possessing better bronchodilatory effects and find out the structure solution by mean of synchrotron powder diffraction.

2,3,4,5-tetrahydroazepino[2,1-*b*]quinazolin-11(1*H*)-one(1) has been studied as a template. In addition, a number of nitrogenous functions were introduced at position 8, 9. The synthesized compounds were studied for their bronchodilatory activity using isolated guinea pig tracheal chain. The 3-D structure is also a key feature to understand their function. In this report, three series asthmatic drug targets structures are successfully solved by synchrotron powder diffraction data and combined simulated annealing method.



(1)

[1] D.P. Jindal, R.S. Bhatti, S. Ahlawat, R. Gupta *Eur.J.Med.Chem.* **2002**, 37, 419

Keywords: structure-aided drug design; structure from powder diffraction; quinazoline

FA5-MS01-P20

Study of the Molecular and Crystalline Structure of Three Nitrogen-Sulphur Pro-Ligands by X-Ray Powder Diffraction and Solid State Dftb Calculations. Asiloé J. Mora^a, Edward E. Ávila^a, Gerzon E. Delgado^a, Andrew N. Fitch^b, Michela Brunelli^c, Ricardo R. Contrera^a, Luis Rincón^a. ^a*Departamento de Química, Facultad de Ciencias, Universidad de Los Andes, Mérida, Venezuela.* ^b*European Synchrotron Radiation Facility, BP220, F-38043 Grenoble CEDEX, France.* ^c*ILL Institut Laue-Langevin, BP 156, 38042 Grenoble cedex 9, France.*

E-mail: asiloe@ula.ve

In the last decades, inorganic chemist has faced the need to mimic the properties of metal sites in metalloproteins to synthesize new catalytic materials with advantageous