

MS23-P16 Facile route for preparation of nanocrystalline ZnMn_2O_4 : effect of preparation conditions on structure and microstructure

Sanja Brkić¹, Jasminka Popović¹, Mirjana Bijelić², Christian Suchomski³, Zora Popović⁴

1. Division for Materials Physics, Ruđer Bošković Institute, Bijenička c. 54, Zagreb, Croatia
2. Department of Physics, Faculty of Science, University of Zagreb, Bijenička c. 32, Zagreb, Croatia
3. Institute of Nanotechnology, Karlsruhe Institute of Technology, Hermann-von-Helmholtz-Platz 1, Eggenstein-Leopoldshafen, Germany
4. Department of Chemistry, Faculty of Science, University of Zagreb, Horvatovac 102A, Zagreb, Croatia

email: sbrkic@irb.hr

Traditional synthesis of spinel materials such as solid-state route involving grinding and firing of a mixture of oxides, nitrates or carbonates which requires elevated temperatures and prolonged process times have been abandoned. Indeed, majority of papers on manganese spinels are focused on low cost preparation methods which proceed at moderate temperatures (600 °C) with enhanced reaction kinetics [1,2]. Interestingly, Liu *et al.* reported a room temperature route for preparation of AMn_2O_4 (A=Zn, Co, Cd) from metal acetates [3]. Although synthetic route proposed by Liu *et al.* represents a facile and very efficient route for low temperature synthesis of spinel materials, in order to utilize this route for the targeted design of nanomaterials it is necessary to establish, very precisely, correlations between specific preparation conditions (concentration of NaOH, aging period, and temperature of additional heat treatments), structure, microstructure and properties. Detailed structural investigation using X-ray powder diffraction (XRPD) and Raman spectroscopy have been carried out in order to correlate specific structural and microstructural features with changes in preparation conditions. ZnMn_2O_4 was prepared by precipitation with NaOH ($c=0.25\text{-}0.8$ M) from solution of Zn and Mn acetates. Also, sample obtained by 0.8 M NaOH was additionally heat treated at $T=300, 400$ and 500 °C. Pronounced difference in crystallinity was observed with increase in concentration of NaOH. Based on the results of Raman spectroscopy a model described by the formula: $[\text{Zn}^{2+}_{1-x}\text{Mn}^{2+}_x]_{\text{tetra}}[\text{Zn}^{2+}_x\text{Mn}^{3+}_{2-2x}\text{Mn}^{4+}_x]_{\text{octa}}\text{O}_4$ has been proposed and tested upon structural data. It was shown, based on Rietveld structure refinement, that unit-cell constants as well as the inversion parameter of spinel lattice increase with the increase in temperature of thermal treatment.

1. L. Hu *et al.*, *Sci. Rep.*, **2**, 217-226, 2012. Y. 2. Li *et al.*, *Nanoscale*, **5**, 2045-2054, 2013. 3. Y. Liu *et al.* *RSC Advances*, **4**, 4727-4731, 2014.

Keywords: manganese spinels, XRPD, microstructure

MS23-P17 Synthesis and characterization of ultrasmall zirconia particles prepared via nonhydrolytic route

Jess E. Gambe¹, Fabien Remondiere¹, Olivier Masson¹, Jenny Jouin¹, Abid Berghout¹, Philippe Thomas¹

1. Science des Procédés Céramiques et de Traitements de Surface (SPCTS), CNRS UMR 7315, Centre Européen de la Céramique, 12 Rue Atlantis, 87068 Limoges Cedex, France

email: jess.gambe@etu.unilim.fr

Zirconia has been applied to various fields in materials science due to its noteworthy electronic, mechanical and thermal properties. These properties become distinctive for ultrasmall particles which are neither that of atomic nor bulk characteristics¹. Structure determination of ultrasmall nanoparticles is at the forefront of modelling their properties and is still at its infancy². In order to help in getting their structural models it is crucial that we synthesize quality ultrasmall particles. However, synthesis of ultrasmall particles with good control over the size and phase purity is not easily done. One way is to use nonhydrolytic route which is advantageous in terms of purity and homogeneity³. In this work, we were able to synthesize well crystallized ultrasmall particles using a modified nonhydrolytic route without surfactants. Average structural and morphological characterizations via classical X-ray diffraction and transmission electron microscopy were done on the samples. Results show that we were able to manipulate the phase purity of our samples from dual phase to single phase. Also, we observed a good control over the size of our particles which are in the nanoscale range from ~ 5.0 to ~ 1.0 nm and appear to have a spherical shape. Furthermore, the modified nonhydrolytic approach allowed us to produce nanoparticles at low temperatures from ~ 210 down to ~ 100 °C with good compositional purity. One of the reasons why we were able to achieve these results is due to the fine tuning of the ratio of precursors to adjust the alkalinity of the solution. Whereas the average structure of our ultrasmall particles is consistent to that of a tetragonal phase zirconia, the atomic-pair distribution function analysis reveal that the particles demonstrate local structural distortions to that of the ideal tetragonal phase zirconia.

References

- [1] M.L. Steigerwald, *et al.*, *Annu.Rev.Mater.Sci.*(1989), **19**, 471-495
- [2] S.J.L. Billinge, *Phys.*(2010) **3**, 25
- [3] P. H. Mutin, *et al.*, *Chem. Mat.*(2009), **21**, 582–596