

## 01-Instrumentation and Experimental Techniques (X-rays, Neutrons, Electrons)

22

The largest resonant enhancements have been observed for incident X-rays near the  $M_{IV}$  absorption edges of the actinides and near the  $L_{III}$  edges of the rare earths and transition metals. The polarization and energy dependence of the resonant cross-section has provided a new spectroscopy of magnetic states which is only beginning to be developed in both scattering and absorption geometries. Current experimental work is reviewed and perspectives related to the operation of new, third generation synchrotron radiation sources are discussed.

**MS-01.04.04 MAGNETIC CIRCULAR X-RAY DICHOISM: PROBING LOCAL MAGNETIC STRUCTURES** by Gisela Schutz, Experimentalphysik II, Universität Augsburg, Germany, and Slike Stahler, Fakultät Physik, E12, Technische Universität München, Germany

Circular magnetic x-ray dichroism in core-level absorption is the absorptive counterpart of magnetic resonance scattering. It is based on the same physical phenomenon, the difference in the imaginary part of the charge scattering amplitude for right and left circularly polarized photons in magnetic matter and a complementary element- and symmetry-selective methods to study the magnetic aspects of the electronic structure of solids. Typical magnetic absorption effects at K- and L-edges in the hard and soft x-ray range are presented. Their relation to the spin polarization of unoccupied bands as well as local magnetic spin and orbital moments are discussed in the frame of single-particle band-structure pictures and atomic multiplet theories. Focusing on magnetic multilayered systems as Co/Pt and Co/Cu it is demonstrated that the magnetic circular dichroism measurements yield important new informations on the exchange coupling mechanism especially the role of the -in the pure element non-magnetic-interlayer.

Also in the EXAFS range, the existence of a magnetic part (SPEXAFS) has been established to be an universal phenomenon, which allows to study local magnetic structures in ferro(magnetic) materials. A comparison of the EXAFS allows a clear distinction between magnetic and nonmagnetic neighborhood also in case of non-magnetic absorbing atoms. Comparing the peak heights in the SPEXAFS strengths for various magnetic systems a direct correlation between the magnetic contribution to the EXAFS and the spin moment of the neighboring atom is found providing a new possibility of a quantitative investigation of local magnetic short-range order.

**MS-01.04.05 SITE SPECIFIC MAGNETIC XANES.** By H. Kawata, Photon Factory, National Laboratory for High Energy Physics, Tsukuba, Japan.

Magnetic X-ray Absorption Near Edge Structure (XANES) using circularly polarized X-rays gives on the spin-polarized unoccupied electron states [1,2]. Recently, the study for ferro- or ferri-magnetic materials by using this experimental method have been rapidly developed. In a case of ferri-magnetic materials, however, there are two different sites for magnetic atoms; for example in the case of  $Y_3Fe_2(FeO_4)_3$  (YIG), the magnetic ions  $Fe^{3+}$  have two different sites. One is an octahedral site and another is a tetrahedral site. The directions of magnetic moments on these sites are opposite to each other. It is naturally expected that the magnetic XANES spectra of Fe K-edge for  $Fe^{3+}$  ion at the octahedral site is different from that for the tetrahedral site, because of the different chemical bonding and the different direction of the magnetic moment. Therefore, it is necessary to identify the site-specific magnetic XANES in order to study these materials. Here we present the first measurement of the site-specific magnetic XANES of YIG by mean of the following two methods.

### <Magnetic XANES under a standing wave field>

The standing wave field method, which is obtained by exiting a dynamical Bragg diffraction in a crystal, gives us site-specific information. Therefore, magnetic XANES measurement under a standing wave field gives us the site-specific magnetic XANES [3]. Figure 1(a) and (b) show the site-specific XANES and magnetic XANES at Fe K-absorption edge. The black dots and open circles in each figures are these of the octahedral site and tetrahedral site, respectively. As shown in this figure, the characteristic structure at the pre-edge is mainly given by the tetrahedral site.

### <Resonant magnetic Bragg scattering>

Recently, Stragier et al. presented the site-specific normal XANES by mean of DAFS [4]. The resonant magnetic Bragg scattering corresponds to the magnetic DAFS. Therefore, the resonant


magnetic Bragg scattering from the different diffraction indexes also brings us the site-specific magnetic XANES. Figure 2(a) and (b) show the results from (444) and (864) diffraction. The structure factor of these indexes are as follows;

$$F(444) = -12f_Y + 8f_{Fe^O} - 12f_{Fe^T},$$

$$F(864) = -8f_Y - 8f_{Fe^T}.$$

Here,  $f_Y$ ,  $f_{Fe^O}$ , and  $f_{Fe^T}$  are atomic form factors of Y, Fe at the octahedral site, and Fe at the tetrahedral site, respectively. In the case of 864 diffraction, Fe at the tetrahedral site only contributes to the structure factor, and the spectrum of Fig. 2(b) is well explained by the magnetic XANES of the tetrahedral site in Fig. 1(b).

- [1] G. Schütz, W. Wagner, W. Wilhelm, P. Kienle, R. Zeller, R. Frahm, and G. Materik, Phys. Rev. Lett. 58 (1987) 737.
- [2] H. Ebert, P. Strange, and B. L. Gyorfly, J. Appl. Phys., 63 (1988) 3055.
- [3] H. Kawata, T. Iwazumi, N. Shiotani, and F. Itoh, The proceedings of international conference on anomalous scattering, 1992 Malente/Hamburg.
- [4] H. Stragier et al. Phys. Rev. Lett. 69(1992)3064.



**PS-01.04.06 MAGNETIC STRUCTURAL STUDIES USING LONG-WAVELENGTH PULSED NEUTRONS.** By J. B. Forsyth, C. J. Carlile and P. S. R. Krisna, Rutherford Appleton Laboratory, Chilton, Oxon. OX11 0QX, U.K.

Powder diffractometers at pulsed neutron sources such as ISIS can provide very high resolutions in backscattering,  $\Delta d/d \sim 5 \times 10^{-4}$ , which are almost constant over the whole range of d-spacings down to  $d \sim 0.3$  Å. Whilst this is very effective for atomic structural studies, it is less adapted to the measurement of magnetic scattering since this intensity falls off rapidly with increasing  $\sin\theta/\lambda$  due to the magnetic form factor. The low order reflections of interest occur at low  $\sin\theta/\lambda$  and are weak due to the paucity of long  $\lambda$  neutrons from the 90 K moderators normally used. We now report measurements in which the incident beam came from a 25 K liquid  $H_2$  moderator. The enhanced long  $\lambda$  flux gives powder patterns having good intensity, excellent