MS13-P09

Theoretical polytypism and practical twinning of aragonite crystals

Pavel Gavryushkin¹, Alexander Re^{*}cnik², Nina Daneu²

- Novosibirsk State University, Laboratory of experimental geochemistry and petrology of the Earth's mantle; Sobolev Institute of Geology and Mineralogy, Laboratory of theoretical and experimental study of high-pressure minerals, Novosibirsk, Russia
- Department for Nanostructured Materials, Jo
 zef Stefan Institute,
 Ljubljana, Slovenia

email: p.gavryushkin@gmail.com

In the present work, we show the results of investigation of aragonite (CaCO₃) microstructure with transmission electron microscopy (TEM) under ambient and elevated temperature, complemented by density functional theory calculations. As objects of investigation we choose crystals from Tazouta (Marocco), Cuenca (Spain), and Koge-Dava (Russia) localities. All crystals were well faceted, 1-3 centimetres length. Different localities were chosen to cover different genesis, morphology and chemistry.

The ubiquitous twinning by {110} down to unit cell size was found on all studied crystals. In some areas twinning is so dense, that these areas can be considered as disordered polytype of aragonite. The super-structural reflections (0.5 0.5 0) were found on [1-10] projection. We suggest that these reflections arise from the diffraction on numerous twinning planes, locally doubling d(110). Also strong reflections prohibited for aragonite symmetry was found in [1-10] projection. Appearance of prohibited reflections can be explained by the presence of flattened domains with decreased symmetry.

Calculated enthalpies of polytypes, produced by ordered twinning by {110}, shows that at 0 K enthalpies of O4-O16 polytypes are even lower than the enthalpy of aragonite. This is consistent with ubiquitous twinning by {110} in both organic and inorganic samples and characterise this twinning as the fundamental feature of aragonite structure. Calculated Gibbs energies indicate that temperature energetically stabilise aragonite relative to other polytypes, which explains absence of ordered polytypes in real crystals.

On heating of powder sample above 350C, satellites reflections appear in [1-10] zone axis. One of the possible explanations of such changes is the generation and ordering of {110} twin boundaries. It was theoretically shown [1] that mechanical twinning taking place during aragonite grinding [2] is realised by the shift of {110} layers of aragonite structure. In our work, we suggest another mechanism of {110} twin boundaries generation, more appropriate for high-temperature conditions.

References:

[1] Liu, J., Huang, Z., Pan, Z., Wei, Q., Li, X., and Qi, Y. (2017). Physical review letters, 118(10), 105501. [2] Shin, Y. A., Yin, S., Li, X., Lee, S., Moon, S., Jeong, J., Kwon, M., Yoo, S. J., Kim, Y.-M., Zhang, T., et al. (2016). Nature communications, 7, 10772, 10772.

Keywords: microstruture, twinning, TEM

MS13-P10

Solid-state synthesis and structural characterization of novel geo-inspired sulfate, Na₂CuM₂(SO₄)₄ (M=Mg, Zn)

Oleg Siidra¹, Diana Nekrasova¹-²; Zhuici Chen¹, Vadim Kovrugin¹-², Olivier Mentre², Marie Colmont²

- 1. Department of Crystallography, St. Petersburg State University, 199034 St. Petersburg, Russia, Saint-Petersburg, Russia
- 2. Unité de Catalyse et Chimie du Solide (UCCS), UMR 8181, Université Lille 1, 59655 Villeneuve d'ASCQ, France

email: siidra@mail.ru

Sulfates attract considerable attention due to their wide distribution in nature. A large group of anhydrous sulfate minerals is formed in high-temperature exhalative processes in fumaroles of volcanoes. Many of the exhalative minerals demonstrate unique structure types and may be of interest from the view point of materials science.

Itelmenite, $Na_2CuMg_2(SO_4)_4$, was recently found in a fumarole of the Naboko scoria cone of the Fissure Tolbachik volcano eruption (2012-2013), Kamchatka Peninsula, Russia [1]. $[M^{2+}_3(SO_4)_4]^{2-}$ sulphate framework in itelmenite is unique and has not been described before in minerals or synthetic compounds. Sulphate tetrahedra are packed into pseudolayered arrangements perpendicular to the *a* axis. Structure topology of itelmenite is rather simple. Each MO_5 or MO_6 polyhedron shares all common corners with sulphate tetrahedra thus forming heteropolyhedral framework with voids filled by Na^+ cations.

Single crystals of Mg- and Zn-dominant synthetic analogues of itelmenite were grown by the solid-state reaction from the mixture containing equimolar quantities of anhydrous CuSO₄, Na₂SO₄, MgSO₄ or ZnSO₄. Na₂CuMg₂(SO₄)₄ (1) and Na₂CuZn₂(SO₄)₄ (2) are orthorhombic, *Pbca*. 1: a = 9.531(6) Å, b = 8.745(6) Å, c = 28.72(2) Å, V = 2393.3(3) Å³. 2: a = 9.458(5) Å, b = 8.811(4) Å, c = 28.850(15) Å, V = 2404(2) Å³. Mixed cationic character of M1, M2 and M3 sites is similar to that observed in natural sample. Symmetrical M3 octahedral site is occupied exclusively by Mg and Zn in the structures of 1 and 2, respectively.

Obtained materials were investigated using powder X-ray diffraction, high-temperature powder X-ray diffraction, IR spectroscopy and DSC-TGA.

This work was financially supported by the Russian Science Foundation through the grant 16-17-10085. Ph.D. of D.O.N. is carried out within the framework of the international French–Russian co-tutorial Ph.D. program. D.O.N. also acknowledges support of the Saint-Petersburg State University through its internal grant. Technical support by the SPbSU X-ray Diffraction Resource Centre is gratefully acknowledged.

References:

[1] Nazarchuk E.V., Siidra O.I., Agakhanov A.A., Lukina E.A., Avdontseva E.Y., Karpov G.A. (2018) Itelmenite, Na2CuMg2(SO4)4, a new anhydrous sulphate mineral from the Tolbachik volcano. Mineralogical Magazine, in press DOI: 10.1180/minmag.2017.081.089.

Keywords: sulphates, minerals, materials