

PS08.01.37 SUPERSTRUCTURE OF THE DEFECT PEROVSKITE TYPE COMPOUNDS $\text{La}_{1/3}\text{NbO}_3$. Y. Tabira, K. Tanabe, K. Suda and N. Ishizawa. Research Laboratory of Engineering Materials, Tokyo Institute of Technology, Nagatsuta, Midori, Yokohama 226, Japan

Superstructure analysis of the title compound (hereafter call LNO) were carried out by the single-crystal X-ray diffraction making use of SR, with the aid of the electron diffraction. The LNO as well as $\text{La}_{1/3}\text{TaO}_3$ (call LTO) are promising host crystals for the Li^+ ion intercalation. Both compounds crystallizes in double-layered perovskite structure with perfectly vacant sites of La^{3+} in the $z=1/2$ plane and by two third occupied sites of La^{3+} in the $z=0$ plane at room temperature. Although reduction of crystal system to which the LNO belongs, from tetragonal (space group $P4/mmm$) to orthorhombic and a superstructure doubling the a and b dimensions of the fundamental tetragonal unit cell, have been previously reported, no structure refinements have been performed to our knowledge. X-ray diffraction experiment were made using the horizontal-type four-circle diffractometer, utilizing SR from a vertical wiggler at the beam line 14A of the PF(KEK) in Tsukuba, Japan. The geometry of the reciprocal lattice of the LNO insists on being orthorhombic unlike the LTO is tetragonal, and the refined cell parameters are $a=0.7817(1)$, $b=0.7836(1)$, $c=0.7910(1)$ nm. Three dimensional diffracted intensity data including the superstructure reflections were collected in the independent reciprocal space within $\sin \theta/\lambda \leq 1.0$ with $\lambda=0.070$ nm. The electron diffraction pattern of the $hk0$ plane of the LNO contained weak but sharp superstructure reflections and obeyed an extinction rule for the C -faced lattice. Of five possible space groups, $Cmnm$, $C2mm$, $Cm2m$, $Cmm2$ and $C222$, $Cm2m$ seems to be the most probable one since in the refinements it gave the lowest conventional R factor to be 0.048 for all 1150 reflections. The R factor is 0.044 for 636 fundamental, and 0.089 for 514 superstructure reflections whose intensities are much weaker than the fundamental ones. Refined structure has an alternate shift along the b axis of La^{3+} in the $z=0$ plane and suggests the statistical fluctuation of Nb^{5+} from the averaged position, which might interact with the local distribution of La^{3+} ions in the structure.

PS08.01.38 NOVEL FERRICENIUM POLYIODIDES. Karl-Friedrich Tebbe, Rita Buchem, Institut für Anorganische Chemie der Universität zu Köln, D-50939 Köln, Greinstraße 6, Germany

Probable ferricenium polyiodides FcI_n ($n > 1$) except for a triiodide FcI_3 [1] are only poorly characterized [2]. During systematic investigations of polyiodide series with suitable cations we proved the compounds of this type with $n = 4, 3, 5, 7, 8, 9, 6, 7$ [3] from which the crystal structures of the ferricenium heptaoidide FcI_7 , [4], the bisferricenium hexadecaoidide $(\text{Fc})_2\text{I}_{16}$ [5] and a triferricenium nonacosaioidide $(\text{Fc})_3\text{I}_{29}$ [6] have been solved. Particularly the latter is worth mentioning ($\text{FcI}_{9,67}$, $P2_1/m$, $Z = 6$, $a = 10.631$ Å, $b = 18.163$ Å, $c = 20.377$ Å, $\beta = 91.31^\circ$, $R = 0.059$), as it is the polyiodide with the largest iodine excess so far [7] containing also hitherto scarcely observed formally three times charged polyiodide ions [8]. Similar reactions of the substituted complexes 1,1'-dimethylferrocene and decamethylferrocene with iodine produce diMeFcI_n with $n = 3$ [9], 5, 7 and decaMeFcI_n with $n = 3, 5, 6, 5$ [10]. These frequently in the anionic iodine part highly connected crystal structures will be presented, described, compared and explained.

- [1] Bernstein, T. & Herbstein, F. H. (1968). *Acta Cryst.* **B24**, 1640.
 [2] Neuse, E. W. & Loonat, M. S. (1985). *J. Organomet. Chem.* **286**, 329.
 [3] Tebbe, K.-F. & Buchem, R. (1995). *Z. Kristallogr. Suppl. Issue 2*, 353.
 [4] Tebbe, K.-F. & Buchem, R. (1995). *Z. Kristallogr.* **210**, 438.
 [5] Tebbe, K.-F. & Buchem, R. (1996). *Z. Kristallogr.*, in print.
 [6] Tebbe, K.-F. & Buchem, R. (1996). *Angew. Chem.*, to be submitted.
 [7] Tebbe, K.-F. (1988). *Z. Kristallogr.* **185**, 496; Tebbe, K.-F., Lindenthal, W. & Farida, T. (1991). *Z. Kristallogr. Suppl. Issue 4*, 203.
 [8] Tebbe, K.-F. (1996). *Z. Kristallogr. Suppl. Issue*, in print.
 [9] Bats, J. W., de Boer, J. J. & Bright, D. (1971). *Inorg. Chim. Acta* **5**, 605.
 [10] Tebbe, K.-F. & Buchem, R., papers in preparation.

PS08.01.39 STRUCTURAL CHEMISTRY OF METAL HYDROGEN SULFATES. S. Troyanov^a, C. Werner^b, E. Kemnitz^b, ^aMoscow State University, Chemistry Department, 119899 Moscow, Vorobjevy Gory, Russia, ^bHumboldt Universität Berlin, Institut für Anorganische Chemie, Hessische Str. 1-2, 10115 Berlin, Germany

A series of new hydrogen sulfates of general formula $\text{M}^I\text{X}_n\text{H}_n\text{SO}_4$ and $\text{M}^{II}\text{Y}_n\text{H}_n\text{SO}_4$ have been synthesized and structurally characterized in the last few years. The general structural aspects are discussed using the value N which defines the average number of hydrogen donor functions (OH groups) per SO_4 tetrahedron.

All crystal structures contain M^{I+} or M^{2+} ions coordinated by O atoms with CN's from 4 to 10 depending mainly on the metal radii. Counterparts consist of simple HSO_4^- tetrahedra or their combination with SO_4^{2-} or H_2SO_4 tetrahedra.

The S-O distances correlate with additional structural functions of O atoms such as coordination by M atom(s), H-acceptor, or H-donor functions. The S-OH distances are generally 0.1 Å longer than the S-O distances. Both S-O and S-OH distances are slightly longer (by 0.02-0.03 Å) in HSO_4^- as compared to those in the H_2SO_4 unit.

Every H atom forms a hydrogen bond O-H...O. The N value in the formula defines the main features of the hydrogen bonding systems: isolated or extended in one, two, or three directions. The connectivity patterns of the H bonding systems for the same N value can vary due to different distribution of acceptor functions between HSO_4^- and H_2SO_4 units.

The structures of α - NaHSO_4 and $\text{Li}[\text{H}(\text{HSO}_4)_2](\text{H}_2\text{SO}_4)_2$ contain disordered hydrogen bonds characterized by strong O...O interactions at the distances of 2.51 Å and 2.44 Å, respectively.

PS08.01.40 $\text{Rb}_2\text{V}_2\text{O}_3(\text{HAsO}_4)_2(\text{H}_2\text{AsO}_4)\cdot\text{H}_2\text{O}$: A MIXED-VALENCE VANADIUM(IV,V) ARSENATE. Wen-Juan Tsai, Sue-Lein Wang*, Department of Chemistry, National Tsing Hua University, Hsinchu, Taiwan 30043

A new mixed-valence vanadium hydrogen arsenate, $\text{Rb}_2\text{V}_2\text{O}_3(\text{HAsO}_4)_2(\text{H}_2\text{AsO}_4)\cdot\text{H}_2\text{O}$ has been synthesized under hydro-thermal conditions and its structure was determined from single-crystal X-ray diffraction data. Intensity measurements were performed on a CCD area detector system. Crystal data: $\text{H}_6\text{As}_3\text{O}_{16}$ Rb_2V_2 , monoclinic, $P2_1/n$, $a = 9.7162(1)$ Å, $b = 11.2839(2)$ Å, $c = 13.8463(2)$ Å, $\beta = 100.843(1)^\circ$, $V = 1490.95(5)$ Å³, $Z = 4$, and $R = 0.0445$ for 2378 unique reflections. The structure is composed of Rb^+ cations, water molecules and $[(\text{V}_4\text{O}_6)(\text{HAsO}_4)_4(\text{H}_2\text{AsO}_4)_2]^{4-}$ cluster anions, in which two of the edge-sharing pairs of VO_6 octahedra are connected by four HAsO_4 and two H_2AsO_4 groups. Variable-temperature powder magnetic susceptibility data confirm the presence of one V^{4+} and one V^{5+} ion per formula unit. In this presentation, the hydrothermal synthesis, single-crystal structure, thermal analysis, and magnetic study of $\text{Rb}_2\text{V}_2\text{O}_3(\text{HAsO}_4)_2(\text{H}_2\text{AsO}_4)\cdot\text{H}_2\text{O}$ will be given. Structural relationship to $\text{A}_2\text{M}_2\text{O}_5(\text{HAsO}_4)_2\cdot\text{H}_2\text{O}$ ($A = \text{Cs}$ and $\text{C}_5\text{H}_5\text{NH}$) is also discussed.