

Hiroyoshi Matsumura^a, Yoshihiro Urade^c, Yasushi Kai^a, ^a*Department of Materials Chemistry, Graduated school of Engineering, University of Osaka.* ^b*New Energy and Industrial Technology Development Organization.* ^c*Department of Molecular Behavioral Biology, Osaka Bioscience Institute.* E-mail: kado@chem.eng.osaka-u.ac.jp

Hematopoietic prostaglandin(PG) D synthase(H-PGDS) is responsible for production of PGD₂ as an allergic or inflammatory mediator in mast cells and Th2 cells[1].

We solved the crystal structure of human H-PGDS bound to the cofactor glutathione(GSH) and HQL-79, a novel inhibitor of H-PGDS in the presence of Ca²⁺ or Mg²⁺, showing the HQL-79 molecule penetrated into the active site between Trp104 and GSH binding site with its biphenyl rings locating at the bottom of the active site, inducing the conformational change of Trp104 with a 60 degree rotation and a 3.7 Å movement of the indole ring.

The surface plasmon resonance analysis revealed that the binding affinity (KD) of HQL-79 is accelerated 10-fold in the presence of both Mg²⁺ and GSH, revealing that the GSH molecule strongly bound in the Mg²⁺-bound form helped the insertion of the HQL-79 molecule, reducing the *K_i* value to be 5 μM with 10-fold in the presence of Mg²⁺. HQL-79 specifically inhibits H-PGDS activities competitive to the substrate PGH₂, and non-competitive to the cofactor GSH[2].

[1] Urade Y., Hayaishi. O., *Vitam Horm*, 2000, **58**, 89-120. [2] Aritake K., et.al., *submitted*.

Keywords: prostaglandins, anti-inflammatory compounds, X-ray structural analysis

P.08.14.38

Acta Cryst. (2005). A61, C349

Polymorphism and Photochromism of Salicylideneaniline

Frédéric Arod^a, Manuel Gardon^a, Philip Pattison^{a,b}, Gervais Chapuis^a, ^a*Laboratoire de Cristallographie, Ecole Polytechnique Fédérale de Lausanne, Switzerland.* ^b*SNBL-ESRF, Grenoble, France.* E-mail: frederic.rod@epfl.ch

Organic compounds exhibiting photo- or thermochromicity have been of considerable interests owing to their properties and possible applications. The photochromism of salicylideneaniline (SA) was discovered by Senier *et al.* at the beginning of last century. In 1964, Cohen *et al.* [1] observed polymorphism.

It is generally accepted that the stable form of SA in the ground state is the enol form, with an intramolecular hydrogen bond between the hydroxyl group and the nitrogen atom. Upon photoexcitation of this enol form with UV light, it undergoes an ultrafast proton transfer from the hydroxyl group to the nitrogen, due to the electronic redistribution in the excited state. The proton transfer generates a keto tautomer in the excited singlet state.

Here, we report on the alpha-2-polymorph structure of SA in the ground state [2], already mentioned by Cohen. We shall also described a new polymorph, beta, which features a planar SA molecule and is therefore thermochromic. Then, we revisit the alpha-1-polymorph structure of SA described by Destro *et al.* [3], but reconsidering their hypothesis. We suggest a lowering of the symmetry with the aim to improve the structure solution.

[1] Cohen M.D., Schmidt G.M.J., Flavian S., *J. Chem. Soc.*, 1964, 2041-2051. [2] Arod F., Gardon M., Pattison P., Chapuis G., *Acta Cryst.*, 2005, *in press*. [3] Destro R., Gavezzotti A., Simonetta M., *Acta Cryst.*, 1978, **B34**, 2867-2869.

Keywords: photochromism, polymorphic structures, properties and structure relationships

P.08.14.39

Acta Cryst. (2005). A61, C349

Structure, Chemical Bonding and Thermoelectric Performance of Zn₄Sb₃

Fausto Cargnoni, Luca Bertini, Carlo Gatti, *CNR-ISTM, Milan, Italy.* E-mail: fausto.cargnoni@istm.cnr.it

Thermoelectricity is due to play an important role in today's energy challenges. The ideal thermoelectric material is a *phonon glass*

and electron crystal, i.e. has a low thermal conductivity combined with high electrical conductivity and Seebeck coefficient. Zinc-antimonide, with formal stoichiometry Zn₄Sb₃, nicely fulfills these requirements, but to explain its unusual combination of properties was not possible because its detailed structure remained for a long time unknown. Now, a crystal structure consistent with the observed mass density has been proposed for the first time by structurally refining single-crystal XRD data, and by analysing powder-synchrotron-radiation diffraction data with a Rietveld-MEM technique.[1,2] Zn₄Sb₃ has a regular Sb lattice, while Zn is distributed over several non-equivalent sites with fractional occupancy. To deconvolute the space-time average inherent to XRD we carried out an extensive computational investigation, and we identified the atomistic arrangements through which the system evolves.[2] In this poster, the bonding and atomic properties of these structures are investigated within the formalism of the Quantum Theory of Atoms In Molecules, and contrasted to the proposed Zintl-phase description of Zn₄Sb₃. [1,2] Furthermore, band-structure calculations of the electronic transport properties are performed to unravel how the atomic structure relates to the material's thermoelectric performance.

[1] Snyder G.J., Christensen M., Nishibori E., Caillat T., Iversen B.B., *Nature Mater.*, 2004, **3**, 458. [2] Cargnoni F., Nishibori E., Rabiller P., Bertini L., Snyder G.J., Christensen M., Gatti C., Iversen B.B., *Chem. Eur. J.*, 2004, **10**, 3861.

Keywords: XRD, ab-initio computations, thermoelectricity

P.08.14.40

Acta Cryst. (2005). A61, C349

Synthetic Chrysotile: Effect of Foreign Ions on the Hydrothermal Synthesis

Isidoro Giorgio Lesci^a, Simone Ferrari^b, Elisabetta Foresti^a, Guido Fracasso^a, Matteo Leoni^c, Norberto Roveri^a, ^a*Department of Chemistry "G.Ciamician", University of Bologna, Italy.* ^b*Department of Earth Sciences, University of Modena – Reggio Emilia, Italy.* ^c*Department of Materials Engineering and Industrial Technologies, University of Trento, Italy.* E-mail: isidorogiorgio.lesci@unibo.it

Conventional and synchrotron radiation X-ray diffraction have been used to characterize chrysotile nano-crystals synthesized under bland hydrothermal conditions. In particular, the effects on the crystallization kinetics of the presence of Al, Fe and Ti species have been evaluated.

Studies were conducted both *in situ* using synchrotron radiation X-ray diffraction at the Daresbury Laboratory station 16.4 and *ex situ* on the material synthesized in a Parr 4652 laboratory reactor.

The synthesis of the material was obtained under conditions usually considered very bland to form complex silicates.

Chemical physical, structural and morphological characterization of the synthesized crystals allowed to know the role of the foreign ions on the observed materials features.

Keywords: nanotubes, chrysotile, hydrothermal synthesis

P.08.14.41

Acta Cryst. (2005). A61, C349-C350

Structural Comparisons of Three Intermetallic Antimonide Families

Evan Lyle Thomas^a, Monica Moldovan^b, David P. Young^b, Julia Y. Chan^a, ^a*Department of Chemistry, Louisiana State University, USA.* ^b*Department of Physics and Astronomy, Louisiana State University, USA.* E-mail: ethoma7@lsu.edu

High quality single crystals of the ternary antimonides LnNi₃Sb₂ (Ln = Y, Gd – Er; x ≈ 0.6) and LnNiSb₃ (Ln = Pr, Nd, Sm) have been grown from an antimony flux. Their crystal structures have been characterized by single crystal X-ray diffraction experiments. The LnNi₃Sb₂ compounds adopt the HfCuSi₂ structure type and crystallize in the tetragonal space group *P4/nmm* with Z = 2 and lattice parameters of a ≈ 4.3 Å, c ≈ 9.3 Å, and V ≈ 170 Å³. These compounds are layered and consist of Ln-capped Sb square nets and Ni tetrahedral frameworks arranged in an anti-PbO fashion. The LnNiSb₃ compounds adopt the CeNiSb₃ structure type and crystallize in the orthorhombic space group, *Pbcm* (No. 57), Z = 12, with lattice