

layers [2], selective broadening of the reflections was observed and occurrence of stacking faults was suggested.

An expression for intensity distribution in powder diffraction from a sample containing stacking faults [3] has been modified in consideration the misfit between two-dimensional lattices of the subsystems, and applied to stacking disorder in composite crystals. The analyses have been made for neutron and X-ray powder patterns of faulted $(\text{Ca}_2\text{CoO}_3)_{0.62}\text{CoO}_2$, and X-ray powder patterns of faulted $(\text{PbS})_{1.12}\text{VS}_2$. The experimental results have been interpreted satisfactorily on the basis of stacking disorder model.

[1] Miyazaki Y., Onoda M., Oku T., Kikuchi M., Ishii Y., Ono Y., Morii Y., Kajitani T., *J. Phys. Soc. Japan*, 2002, **71**, 491. [2] Onoda M., Kato K., Gotoh Y., Oosawa Y., *Acta Cryst.*, 1990, **B46**, 487. [3] Onoda M., Saeki M., Kawada I., *Acta Cryst.*, 1980, **A36**, 952.

Keywords: composite crystals, stacking faults, diffuse scattering

P.22.02.2

Acta Cryst. (2005). **A61**, C476

5-D Modeling of the Co-rich decagonal Al-Co-Ni Quasicrystal

Sofia Deloudi, Walter Steurer, Laboratory of Crystallography, ETH Zurich, Switzerland. E-mail: deloudi@mat.ethz.ch

Even twenty years after the discovery of quasicrystals, not a single structure is known with the accuracy and reliability commonly expected for regular periodic structures [1]. One way leading towards understanding the structure of quasicrystals, is given by the examination of approximants.

The main interest of this work is to investigate the complete stability field of decagonal Al-Co-Ni by 5-D modeling, starting from the W-phase [2]. The latter is of particular interest, as it is the only known approximant in this system, containing the complete atomic cluster [3]. The focus will be on order, disorder and phase transformations of the decagonal Al-Co-Ni.

First 5-D modeling results of the Co-rich decagonal phase will be discussed. Via embedding the W-phase, models of the decagonal phase are rendered and phasonic modes are being applied.

[1] Steurer W., *Z. Kristallogr.*, 2004, **219**, 391. [2] Hiraga K., Ohsuna T., Nishimura S., *J. Alloy Comp.*, 2001, **325**, 145-150. [3] Sugiyama K., Nishimura S., Hiraga K., *J. Alloy Comp.*, 2002, **342**, 65-71.

Keywords: quasicrystal, 5-D modeling, W-phase

P.22.02.3

Acta Cryst. (2005). **A61**, C476

Modulated Structure of $[\text{FeCl}(\text{DMPE})_2(\text{NCC}_6\text{H}_4\text{NO}_2)][\text{PF}_6]$ a Material for Use in NLO

Leo Straver^a, V. Petricek^b, M. T. Duarte^c, M. F. M. da Piedadec, M. P. Robalo^c, A. P. S. Teixeira^c, M. H. Garcia^c, ^a*Bruker AXS B.V., Delft, Netherlands.* ^b*Acad Sci Czech Republ, Inst Phys, Prague, Czech Republic.* ^c*Centro de Química Estrutural, IST, Lisboa, Portugal.* E-mail: leo.straver@bruker-axs.nl

It is well known the recent interest in the nonlinear optical (NLO) properties of organometallic complexes [1,2]. Most efficient NLO-active complexes have a dipolar composition, with an electron-donating group linked by a π -conjugated bridge to an electron-accepting group. Our studies on complexes with this composition have been focused on metal σ -nitriles, for which the second-order NLO responses have been determined [3,4]. Since, it is also of interest to assess the importance of co-ligands in the donor metal coordination sphere, our attention has turned to an alternative coordinated Fe(II) system, namely trans-chloro(diphosphine)iron nitriles. In the solid state our main interest is to align the molecules and avoid centrosymmetric space groups. When trying to solve the structure of the title complex we had several difficulties and the structure proved to be modulated. Refinements are being done using JANA and final results will be presented in this work.

[1] Whittall I.R., et al. *Adv. Organomet. Chem.*, 1999, **43**, 349. [2] Goovaerts E., et al. *Handbook of Advanced Electronic and Photonic Materials*, Ed. H.S. Nalwa, 2001, **9**, Ch. 3, 127. [3] Wenseleers W. et al. *J. Mater.Chem.*, 1998, **8**, 925. [4] Garcia M.H., Robalo M.P., Teixeira A.P.S., Piedade M.F.M., Duarte M.T., Dias A.R., *J. Organomet. Chem.*, 2001, **632**, 145.

Keywords: NLO, organometallic compound, modulated structure

P.22.02.4

Acta Cryst. (2005). **A61**, C476

Dislocation Dynamics in a Dodecagonal Quasiperiodic System

Ron Lifshitz, Gilad Barak, *School of Physics & Astronomy, Tel Aviv University, Israel.* E-mail: ronlif@gmail.com

We have developed a set of numerical tools for the quantitative analysis of defect dynamics in quasiperiodic structures, with the intention of addressing some of the open questions regarding the dynamics of dislocations in quasicrystals. We are applying these tools to study dislocation motion in the dynamical equation of Lifshitz and Petrich [1] whose steady state solutions are quasiperiodic, exhibiting dodecagonal symmetry.

Here we demonstrate - by showing real-time computer simulations - our ability to inject an arbitrary set of dislocations, parameterized by the homotopy group of the D-torus, and quantitatively follow the positions of these dislocations as the equation evolves in real time. We measure and analyze the dislocation velocity as a function of applied stress and shear, as well as the phonon and phason strains that accompany this motion as the system evolves in time. These results display intriguing differences with respect to the behavior of dislocations in periodic solutions of the dynamical equation.

[1] Lifshitz R., Petrich D.M., *Phys. Rev. Lett.*, 1997, **79**, 1261.

Keywords: dislocation dynamics, quasicrystals, computer simulation

P.22.03.1

Acta Cryst. (2005). **A61**, C476

Ab initio Simulations on the W-phase of the Al-Co-Ni System

Kai H. Hassdenteufel, Walter Steurer, Artem R. Oganov, *Laboratory of Crystallography, Department of Materials, ETH Zurich, Switzerland.* E-mail: kai.Hassdenteufel@mat.ethz.ch

The W-phase [1] is the highest stable approximant of the decagonal quasicrystal known in the system Al-Co-Ni. Its structure contains the so-called "20 Å-cluster", which is a characteristic building unit of decagonal Al-Co-Ni.

The Co/Ni ratio determines which modification of decagonal $\text{Al}_{72}\text{Co}_{28-x}\text{Ni}_x$ ($8 \leq x \leq 20$) is formed. Therefore, we studied the influence of the Co/Ni ratio on the structure of the W-phase, starting from binary compositions Al-Co and Al-Ni with idealized positions. From these results a realistic ternary model was derived.

The structure models were optimized using the VASP code [2,3]. Our calculations are based on the generalized gradient approximation and utilized PAW potentials [4] supplied with VASP. The band structure, electron density distribution and electron localization function were calculated.

These calculations help to get insight into the factors governing formation and stability of this kind of complex intermetallic alloy. They also corroborate the results of the single-crystal X-ray structure analysis, from which a significantly distorted and disordered structure model was obtained.

[1] Sugiyama K., Nishimura S., Hiraga K., *Jour. Alloys Comp.*, 2002, **342**. [2] Kresse G., Furthmüller J., *Comput. Mat. Sci.*, 1996, **6**. [3] Kresse G., Furthmüller J., *Phys. Rev. B*, 1996, **54**. [4] Kresse G., Joubert J., *Phys. Rev. B*, 1999, **59**.

Keywords: quasicrystals, ab initio calculations, clusters

P.22.03.2

Acta Cryst. (2005). **A61**, C476-C477

Interaction and Phase Transitions in a Potototype Self-assembled Supramolecular Aperiodic Crystal

Bertrand Toudic^a, L. Bourgeois^{a,b}, C. Ecolivet^a, P. Garcia^a, P. Bourges^b, T. Brewczewski^c, ^a*G.M.C.M, UMR CNRS 6626, Université de Rennes 1, F-35042 Rennes.* ^b*L.L.B., CEA-CNRS, CE-Saclay, F-91191 Gif/Yvette.* ^c*Facultad de Ciencias, Apdo 644, Bilbao, Spain.* E-mail: bertrand.toudic@univ-rennes1.fr

This contribution reports on very new structural and physical