FA2-MS19-P01

High-pressure behavior of bismuth iron oxide Bi₂Fe₄O₉. Jasmin Biehler^a, Alexandra Friedrich^a, Wolfgang Morgenroth^a, Leonore Wiehl^a, Björn Winkler^a, Michael Hanfland^b, Martin Tolkiehn^c, Manfred Burianek^d, Manfred Mühlberg^d. ^aInst. of Geosciences, Crystallography, Goethe-University Frankfurt am Main, Germany. ^bESRF, Grenoble, France. ^cDESY/HASYLAB, Hamburg, Germany. ^dInst. of Crystallography, University of Cologne, Germany. E-mail: biehler@kristall.uni-frankfurt.de

 $Bi_2Fe_4O_9$ belongs to the mullite-related compounds $Bi_2M_4O_9$ (with M = Fe, Al, Ga) [1]. It melts incongruently and single crystals were grown from high temperature solutions using the top seeded solution growth method (TSSG) [2]. Bi₂Fe₄O₉ has interesting magnetic properties and shows a magnetic transition at about 264 K from paramagnetism to antiferromagnetism [3]. We are interested in the behaviour of the stereochemically active Bi3+ lone electron pair, which exists in the crystal structure of the compounds, at ambient and high pressure and of the effect of cation substitution on the compressibility and the occurrence of a reversible phase transition. In this study, the high-pressure behaviour of Bi₂Fe₄O₉ was analysed by in-situ powder and single-crystal Xray diffraction and Raman spectroscopy. Pressures up to 34.33(8) GPa were generated using the diamond anvil cell technique. The occurrence of a reversible phase transition, analogous to that observed in isotypic $Bi_2Ga_4O_9$ [4,5] from space group *Pbam* to *Pbnm* (with c' = 2c) was confirmed in Bi₂Fe₄O₉ at 6.89(6) GPa from powder diffraction experiments and validated with Raman measurements. The high-pressure structure is stable at least up to 26.3(1) GPa. A fit of a 2ndorder Birch-Murnaghan equation of state to the p-V data results in $K_0 = 74(3)$ GPa for the low-pressure phase and 79(2) GPa for the high-pressure phase. The Grüneisen-parameters for several modes are obtained from the Raman-spectroscopic measurements. The crystal structures of the low- and highpressure phases were refined from single-crystal data at ambient conditions and at 100 K and at pressures of 4.49(2), 6.46(2), 7.1(1), 7.26(2) and 9.4(1) GPa. The influence of cation substitution on the high-pressure stability of the $Bi_2M_4O_9$ compounds will be discussed.

Schneider H., Komarneni S. (Eds.), Wiley-VCH, p. 1-140, 2005.
Burianek M., Mühlberg M., Woll M., Schmücker M., Gesing T.M., and Schneider H., Cryst. Res. Technol. 44 1156-1162 (2009).
Shamir N., Gurewitz E., Shaked H. Acta Cryst., A34, 662-666, 1978.
López-de-la-Torre L., Friedrich A., Juarez-Arellano E.A., Winkler B., Wilson D.J., Bayarjargal L., Hanfland M., Burianek M., Mühlberg M. and Schneider H. J.Solid State Chem., 182 (4):767–777, 2009.
Friedrich A., Juarez-Arellano E.A., Haussühl E., Boehler R., Winkler B., Wiehl L., Morgenroth W., Burianek M. and Mühlberg M. Acta Cryst. B, 2010 (in press).

Keywords: high-pressure X-ray diffraction, Raman spectroscopy, diamond anvil cells

FA2-MS19-P02

Self-assembly of fundamental building blocks (FBB) in borate structures. Rimma Bubnova^a, Stanislav Filatov^b. ^a*Institute of Silicate Chemistry of the RAS, St. Petersburg, Russia.* E-mail: rimma bubnova@mail.ru One of distinguishing characteristic of unique borate crystal chemistry is occurrence of rigid groups consisting of the BO₃ triangles and the BO₄ tetrahedra (nanogroups about 0.6-1 nm). These rigid groups that constitute the fundamental building blocks (FBBs) maintain their configuration in various crystal structures without any essential changes. Moreover it is shown [1, 2] that on heating the BO₃ and BO₄ polyhedra and the FBBs maintain the size and configuration also. The great diversity of borate crystal structures arises from FBBs condensed to form structures of 0D-, 1D-, 2D and 3D-dimensionality. Here we present self-assembly of FBBs in borate structures as a result of thermal vibrations of boron and oxygen atoms and FBBs.

In a BO₃ triangle oxygen and boron atoms oscillate mainly perpendicular to the B-O bond. There are three B-O bonds in the BO3 triangle, thus B and O atoms vibrate maximally perpendicular to the BO₃ plane. In the case of a triborate group composed of three triangles B and O atoms vibrate maximally perpendicular to the plane of the triborate group. Hence a structure with isolated triborate groups expands greatly perpendicular to plane of a group and expands weakly in parallel to plane of a group: as example we examine the same character of thermal expansion of α - and β -BaB₂O₄ crystal structures built up from isolated triborate groups. Moreover the triborate groups are usually self-arranged by parallel to each other in the 0D-3B-structures. Similar situation occurs in structures with isolated tetra- and pentagroups although in last case the internal oxygen and boron atoms of both single rings vibrate perpendicular to planes of these rings group while a group as a whole oscillates relative axis of the group – the line drawn parallel to the plane of both rings. From this viewpoint we examine the role of thermal vibrations anisotropy in borate structure formation any dimensionality.

The studies are supported by the Russian Found the Basic Research (project # 08-03-00232).

[1] Bubnova R.S., Filatov S.K. *Phys. Stat. Sol.* 2008, 245(b), 2469. [2] Bubnova R.S., Filatov S.K. High-Temperature Crystal Chemistry of Borates and Borosilicates. 2008, St. Petersburg, Nauka (in Russ.).

Keywords: high-temperature crystal chemistry, borates, thermal expansion, single-crystal and powder hightemperature diffraction

FA2-MS19-P03

Studies on the decomposition of tungsten hexacarbonyl, W(CO)₆. <u>Nadine Rademacher</u>^a, Lkhamsuren Bayarjargal^a, Björn Winkler^a, Hyunjeong Kim^b, Katharine Page^b, Thomas Proffen^b. ^aInst. of Geosciences, University of Frankfurt, Germany. ^bLos Alamos National Laboratory, Lujan Neutron Scattering Center, USA.

E-mail: Rademacher@kristall.uni-frankfurt.de

Tungsten hexacarbonyl is an important precursor molecule for the synthesis of micro- or nanocrystalline tungsten and tungsten compounds. In electron- or ion-beam deposition techniques, $W(CO)_6$ is used as a precursor for mask repair or nanolithography.^[1] In order to better understand $W(CO)_6$ and its behaviour at a variety of reaction conditions, our group performed decomposition experiments in a laser heated diamond anvil cell (DAC) with pressures up to 17 GPa. Additional experiments at lower pressures and temperatures were performed in an autoclave. The decomposition products of $W(CO)_6$ have been characterised using Raman