

## Silver europium(III) polyphosphate

 Mounir Ayadi,<sup>a\*</sup> Mokhtar Férid<sup>b</sup> and Bernard Moine<sup>c</sup>
<sup>a</sup>Laboratoire d'Application de la Chimie aux Ressources et, Substances Naturelles et à l'Environnement, Faculté des Sciences de Bizerte, 7021 Zarzouna Bizerte, Tunisia,

<sup>b</sup>Unité de Recherches de Matériaux de Terres Rares, Centre National de Recherches en Sciences des Matériaux, BP 95 Hammam-Lif 2050, Tunisia, and <sup>c</sup>LPCLM-UMR 5620 CNRS/UCBL, Domaine Scientifique de la Doua, Université Claude Bernard Lyon 1 Batiment Alfred Kastler, 10 rue André-Marie Ampère, 69622 Villeurbanne Cedex, France

Correspondence e-mail: Mounir.Ayadi@ism.mu.tn

Received 14 December 2008; accepted 3 February 2009

 Key indicators: single-crystal X-ray study;  $T = 298$  K; mean  $\sigma(\text{P}-\text{O}) = 0.005$  Å;  $R$  factor = 0.042;  $wR$  factor = 0.109; data-to-parameter ratio = 12.3.

Europium(III) silver polyphosphate,  $\text{AgEu}(\text{PO}_3)_4$ , was prepared by the flux method. The atomic arrangement is built up by infinite  $(\text{PO}_3)_n$  chains (periodicity of 4) extending along the  $c$  axis. These chains are joined to each other by  $\text{EuO}_8$  dodecahedra. The  $\text{Ag}^+$  cations are located in the voids of this arrangement and are surrounded by five oxygen atoms in a distorted [4+1] coordination.

### Related literature

For isotypic  $\text{AgNd}(\text{PO}_3)_4$ , see: Trunov *et al.* (1990). For related structures, see: Yamada *et al.* (1974); Hashimoto *et al.* (1991); Horchani *et al.* (2003); Durif (1995); Averbuch-Pouchot & Bagieu-Boucher (1987); Férid (2006).

### Experimental

#### Crystal data

 $\text{AgEu}(\text{PO}_3)_4$ 
 $M_r = 575.72$ 

 Monoclinic,  $P2_1/n$ 
 $a = 9.9654$  (3) Å

 $b = 13.1445$  (7) Å

 $c = 7.2321$  (3) Å

 $\beta = 90.42$  (1)°

 $V = 947.31$  (7) Å<sup>3</sup>
 $Z = 4$ 

 Mo  $K\alpha$  radiation

 $\mu = 9.37$  mm<sup>-1</sup>
 $T = 298$  (2) K

 $0.19 \times 0.18 \times 0.17$  mm

#### Data collection

Nonius KappaCCD diffractometer

Absorption correction: multi-scan

 (*SADABS*; Sheldrick, 1996)

 $T_{\min} = 0.167$ ,  $T_{\max} = 0.201$ 

3371 measured reflections

2019 independent reflections

 1704 reflections with  $I > 2\sigma(I)$ 
 $R_{\text{int}} = 0.042$ 

#### Refinement

 $R[F^2 > 2\sigma(F^2)] = 0.042$ 
 $wR(F^2) = 0.109$ 
 $S = 1.03$ 

2019 reflections

164 parameters

 $\Delta\rho_{\max} = 2.43$  e Å<sup>-3</sup>
 $\Delta\rho_{\min} = -2.06$  e Å<sup>-3</sup>

Data collection: *COLLECT* (Nonius, 2001); cell refinement: *DENZO/SCALEPACK* (Otwinowski & Minor, 1997); data reduction: *DENZO/SCALEPACK*; program(s) used to solve structure: *SHELXS97* (Sheldrick, 2008); program(s) used to refine structure: *SHELXL97* (Sheldrick, 2008); molecular graphics: *DIAMOND* (Brandenburg, 1998); software used to prepare material for publication: *SHELXL97*.

This work is supported by the Ministry of Higher Education, Scientific Research and Technology of Tunisia.

Supplementary data and figures for this paper are available from the IUCr electronic archives (Reference: BR2089).

### References

- Averbuch-Pouchot, M. T. & Bagieu-Boucher, M. (1987). *Z. Anorg. Allg. Chem.* **552**, 171–180.
- Brandenburg, K. (1998). *DIAMOND*. University of Bonn, Germany.
- Durif, A. (1995). In *Crystal Chemistry of Condensed Phosphates*. New York: Plenum Press.
- Férid, M. (2006). In *Etude des propriétés cristallographiques et physiques des phosphates condensés de terres rares*. Paris: Publibook.
- Hashimoto, N., Takada, Y., Sato, K. & Ibuki, S. (1991). *J. Lumin.* **48–49**, 893–897.
- Horchani, K., Gâcon, J. C., Férid, M., Trabelsi-Ayadi, M., Krachni, G. K. & Liu, G. K. (2003). *Opt. Mater.* **24**, 169–174.
- Nonius (2001). *COLLECT*. Nonius BV, Delf, The Netherlands.
- Otwinowski, Z. & Minor, W. (1997). *Methods in Enzymology*, Vol. 276, *Macromolecular Crystallography, Part A*, edited by C. W. Carter Jr & R. M. Sweet, pp. 307–326. New York: Academic Press.
- Sheldrick, G. M. (1996). *SADABS*. University of Göttingen, Germany.
- Sheldrick, G. M. (2008). *Acta Cryst.* **A64**, 112–122.
- Trunov, V. K., Anisimova, N. Yu., Karmanovskaya, N. B. & Chudinova, N. N. (1990). *Izv. Akad. Nauk SSSR Neorg. Mater.* **26**, 1288–1290.
- Yamada, T., Otsuka, K. & Nakano, J. (1974). *Appl. Phys.* **45**, 5096–5097.

## supporting information

*Acta Cryst.* (2009). E65, i13 [doi:10.1107/S1600536809004085]

## Silver europium(III) polyphosphate

Mounir Ayadi, Mokhtar Férid and Bernard Moine

### S1. Comment


In the last decades, investigation of the synthesis and characterization of rare earth polyphosphates has gained much attention due to their potential applications in diverse areas such as phosphors and laser materials (Yamada *et al.*, 1974; Hashimoto *et al.*, 1991; Horchani *et al.*, 2003). In aim to study the condensed phosphates of rare earth and monovalent cations of general formula  $MILn(PO_3)_4$  (with MI = monovalent cation)(Durif, 1995), ( $L_n = \text{Eu, Er, Yb}$ ), we have synthesized single crystals of silver europium polyphosphate and investigated its crystalline structure. The atomic arrangement of this structure is characterized by a three-dimensional framework built of  $(PO_3)_n$  chains that are formed by corner-sharing of  $PO_4$  tetrahedra.  $\text{Eu}^{3+}$  and  $\text{Ag}^+$  cations alternate in the middle of four such chains with  $\text{Eu—Ag}$  distances of 3.64 (7) Å (figures 1,3). The  $\text{EuO}_8$  dodecahedra are isolated from each other and the distances  $\text{Eu—O}$  are arranged in interval 2.355 (5)- 2.508 (5)Å (figure 2). The polyphosphate chains display two types of distances,  $\text{P—O}$  terminal ranging from 1.479 (5) to 1.505 (5)Å and  $\text{P—O}$  bridging, ranging from 1.585 (5)to 1.609 (5)Å. These distances are comparable with those reported for other condensed phosphates (Durif, 1995; Averbuch-Pouchot & Bagieu Beucher, 1987; Férid (2006). The structural study reported for silver neodymium polyphosphate  $\text{AgNd}(PO_3)_4$  (Trunov *et al.*, 1990) showed that the compound crystallize in the  $P2_1/n$  space group and has similar unit cell parameters compared to  $\text{AgEu}(PO_3)_4$ .

### S2. Experimental


Single crystals of  $\text{AgEu}(PO_3)_4$  were prepared by flux method. A mixture of  $\text{Ag}_2\text{CO}_3$  (3 g),  $\text{EuCl}_3 \cdot 6\text{H}_2\text{O}$  (0.5 g) and  $\text{H}_3\text{PO}_4$ (85%, 17 ml), was progressively heated in a vitreous carbon crucible to 473 K for 12 h. The temperature was then raised and kept at 600 K for 16 days after that, the furnace was slowly cooled until the room temperature. The product was washed with boiling water to separate colorless single crystals from phosphoric acid.

### S3. Refinement


The highest peak and the deepest hole are located 1.22Å and 0.73 Å, respectively, from Ag and Eu.

**Figure 1**

The structural arrangement of  $\text{AgEu}(\text{PO}_3)_4$  along  $a$  axis.



**Figure 2**  
Projection of  $\text{EuO}_8$  dodecahedra viewed along  $[0\ 0\ 1]$  direction.



**Figure 3**  
The sequence of  $\text{PO}_4$  tetrahedra in  $\text{AgEu}(\text{PO}_3)_4$ , with displacement ellipsoids drawn at the 50% probability level.  
[Symmetry codes: (i)  $1-x, 2-y, 2-z$ ; (ii)  $1-x/2, 2-y, 3-z$ ]

## Europium(III) silver polyphosphate

## Crystal data

AgEu(PO<sub>3</sub>)<sub>4</sub> $M_r = 575.72$ Monoclinic,  $P2_1/n$ 

Hall symbol: -P 2yn

 $a = 9.9654$  (3) Å $b = 13.1445$  (7) Å $c = 7.2321$  (3) Å $\beta = 90.42$  (1)° $V = 947.31$  (7) Å<sup>3</sup> $Z = 4$  $F(000) = 1064$  $D_x = 4.037$  Mg m<sup>-3</sup>Mo  $K\alpha$  radiation,  $\lambda = 0.71073$  Å

Cell parameters from 25 reflections

 $\theta = 2.4$ – $30.1$ ° $\mu = 9.37$  mm<sup>-1</sup> $T = 298$  K

Prism, colorless

 $0.19 \times 0.18 \times 0.17$  mm

## Data collection

Nonius KappaCCD

diffractometer

Radiation source: fine-focus sealed tube

Graphite monochromator

 $\varphi$  and  $\omega$  scans

Absorption correction: multi-scan

(SADABS; Sheldrick, 1996)

 $T_{\min} = 0.167$ ,  $T_{\max} = 0.201$ 

3371 measured reflections

2019 independent reflections

1704 reflections with  $I > 2\sigma(I)$  $R_{\text{int}} = 0.042$  $\theta_{\max} = 27.5$ °,  $\theta_{\min} = 3.8$ ° $h = -12 \rightarrow 12$  $k = -16 \rightarrow 15$  $l = -9 \rightarrow 9$ 

## Refinement

Refinement on  $F^2$ 

Least-squares matrix: full

 $R[F^2 > 2\sigma(F^2)] = 0.042$  $wR(F^2) = 0.109$  $S = 1.03$ 

2019 reflections

164 parameters

0 restraints

Primary atom site location: structure-invariant

direct methods

Secondary atom site location: difference Fourier map

 $w = 1/[\sigma^2(F_o^2) + (0.0685P)^2 + 1.0941P]$ where  $P = (F_o^2 + 2F_c^2)/3$  $(\Delta/\sigma)_{\max} < 0.001$  $\Delta\rho_{\max} = 2.43$  e Å<sup>-3</sup> $\Delta\rho_{\min} = -2.06$  e Å<sup>-3</sup>Extinction correction: SHELXL08 (Sheldrick, 2008),  $F_c^* = kF_c[1 + 0.001x F_c^2 \lambda^3 / \sin(2\theta)]^{-1/4}$ 

Extinction coefficient: 0.00014 (2)

## Special details

**Geometry.** All e.s.d.'s (except the e.s.d. in the dihedral angle between two l.s. planes) are estimated using the full covariance matrix. The cell e.s.d.'s are taken into account individually in the estimation of e.s.d.'s in distances, angles and torsion angles; correlations between e.s.d.'s in cell parameters are only used when they are defined by crystal symmetry. An approximate (isotropic) treatment of cell e.s.d.'s is used for estimating e.s.d.'s involving l.s. planes.

**Refinement.** Refinement of  $F^2$  against ALL reflections. The weighted  $R$ -factor  $wR$  and goodness of fit  $S$  are based on  $F^2$ , conventional  $R$ -factors  $R$  are based on  $F$ , with  $F$  set to zero for negative  $F^2$ . The threshold expression of  $F^2 > \sigma(F^2)$  is used only for calculating  $R$ -factors(gt) etc. and is not relevant to the choice of reflections for refinement.  $R$ -factors based on  $F^2$  are statistically about twice as large as those based on  $F$ , and  $R$ -factors based on ALL data will be even larger.

Fractional atomic coordinates and isotropic or equivalent isotropic displacement parameters (Å<sup>2</sup>)

	$x$	$y$	$z$	$U_{\text{iso}}^*/U_{\text{eq}}$
Eu	0.52254 (4)	0.78212 (2)	0.51227 (4)	0.01862 (19)
Ag	0.43355 (7)	0.77670 (5)	1.00017 (8)	0.0322 (2)
P1	0.25190 (18)	0.90008 (12)	1.2536 (2)	0.0168 (4)
P2	0.19511 (18)	0.87338 (12)	1.6486 (2)	0.0167 (4)

P3	0.79921 (18)	0.90983 (12)	1.2635 (2)	0.0172 (4)
P4	0.73739 (18)	0.88594 (12)	0.8738 (2)	0.0162 (4)
O1	0.1995 (5)	0.8356 (3)	1.1018 (6)	0.0241 (11)
O2	0.3997 (5)	0.8951 (4)	1.2904 (7)	0.0243 (11)
O3	0.2039 (5)	1.0133 (3)	1.2168 (7)	0.0240 (11)
O4	0.1629 (5)	0.8769 (3)	1.4335 (6)	0.0198 (10)
O5	0.3444 (5)	0.8678 (4)	1.6767 (7)	0.0218 (10)
O6	0.1062 (6)	0.7906 (3)	1.7231 (6)	0.0228 (11)
O7	0.8644 (5)	1.0214 (3)	1.2777 (7)	0.0193 (10)
O8	0.9144 (5)	0.8395 (3)	1.2329 (6)	0.0236 (10)
O9	0.7055 (5)	0.8919 (3)	1.4217 (6)	0.0218 (10)
O10	0.7085 (5)	0.9202 (3)	1.0822 (6)	0.0203 (10)
O11	0.8483 (5)	0.8097 (3)	0.8671 (7)	0.0218 (10)
O12	0.6047 (5)	0.8557 (3)	0.7933 (6)	0.0198 (10)

*Atomic displacement parameters (Å<sup>2</sup>)*

	$U^{11}$	$U^{22}$	$U^{33}$	$U^{12}$	$U^{13}$	$U^{23}$
Eu	0.0183 (3)	0.0189 (2)	0.0186 (2)	−0.00063 (12)	−0.00048 (15)	−0.00108 (12)
Ag	0.0262 (4)	0.0456 (4)	0.0249 (3)	0.0034 (2)	0.0008 (2)	−0.0088 (2)
P1	0.0201 (9)	0.0138 (7)	0.0165 (7)	−0.0001 (6)	0.0005 (6)	0.0001 (6)
P2	0.0173 (9)	0.0155 (8)	0.0173 (8)	0.0007 (6)	−0.0001 (6)	−0.0002 (6)
P3	0.0206 (9)	0.0143 (7)	0.0168 (8)	0.0004 (6)	−0.0017 (6)	−0.0002 (6)
P4	0.0162 (9)	0.0160 (8)	0.0165 (8)	−0.0001 (6)	−0.0020 (6)	−0.0012 (6)
O1	0.034 (3)	0.019 (2)	0.019 (2)	0.004 (2)	−0.002 (2)	−0.0060 (19)
O2	0.023 (3)	0.026 (2)	0.023 (2)	0.000 (2)	−0.002 (2)	−0.002 (2)
O3	0.028 (3)	0.016 (2)	0.028 (3)	0.007 (2)	−0.004 (2)	0.0052 (19)
O4	0.019 (3)	0.025 (2)	0.016 (2)	0.0000 (19)	−0.0004 (18)	0.0039 (18)
O5	0.017 (3)	0.024 (2)	0.025 (2)	0.0021 (19)	−0.003 (2)	−0.007 (2)
O6	0.029 (3)	0.021 (2)	0.018 (2)	−0.005 (2)	0.000 (2)	0.0038 (18)
O7	0.013 (2)	0.014 (2)	0.031 (3)	−0.0005 (18)	0.0063 (19)	−0.003 (2)
O8	0.027 (3)	0.018 (2)	0.026 (2)	0.003 (2)	−0.001 (2)	−0.002 (2)
O9	0.027 (3)	0.023 (2)	0.016 (2)	−0.004 (2)	0.0040 (19)	−0.0026 (18)
O10	0.017 (2)	0.020 (2)	0.024 (2)	0.0009 (19)	−0.0016 (18)	−0.0023 (19)
O11	0.022 (3)	0.018 (2)	0.025 (2)	0.007 (2)	−0.001 (2)	0.002 (2)
O12	0.023 (3)	0.021 (2)	0.015 (2)	0.005 (2)	−0.0053 (19)	−0.0005 (18)

*Geometric parameters (Å, °)*

Eu—O11 <sup>i</sup>	2.355 (5)	P2—O4	1.587 (5)
Eu—O12	2.390 (4)	P2—O7 <sup>vi</sup>	1.598 (5)
Eu—O9 <sup>ii</sup>	2.420 (5)	P3—O8	1.492 (5)
Eu—O5 <sup>ii</sup>	2.422 (5)	P3—O9	1.500 (5)
Eu—O1 <sup>iii</sup>	2.430 (5)	P3—O10	1.593 (5)
Eu—O6 <sup>iv</sup>	2.451 (5)	P3—O7	1.607 (5)
Eu—O2 <sup>ii</sup>	2.500 (5)	P4—O11	1.493 (5)
Eu—O8 <sup>i</sup>	2.508 (5)	P4—O12	1.495 (5)
Eu—Ag	3.6453 (7)	P4—O3 <sup>vii</sup>	1.592 (5)

Eu—Ag <sup>ii</sup>	3.8025 (7)	P4—O10	1.602 (5)
Ag—O8 <sup>i</sup>	2.470 (5)	O1—Eu <sup>viii</sup>	2.430 (5)
Ag—O12	2.503 (5)	O2—Eu <sup>v</sup>	2.500 (5)
Ag—O6 <sup>iii</sup>	2.511 (5)	O3—P4 <sup>vii</sup>	1.592 (5)
Ag—O1	2.570 (5)	O5—Eu <sup>v</sup>	2.422 (5)
Ag—Eu <sup>v</sup>	3.8025 (7)	O6—Eu <sup>ix</sup>	2.451 (5)
P1—O1	1.479 (5)	O6—Ag <sup>viii</sup>	2.511 (5)
P1—O2	1.496 (6)	O7—P2 <sup>vi</sup>	1.598 (5)
P1—O3	1.585 (5)	O8—Ag <sup>x</sup>	2.470 (5)
P1—O4	1.609 (5)	O8—Eu <sup>x</sup>	2.508 (5)
P2—O5	1.502 (5)	O9—Eu <sup>v</sup>	2.420 (5)
P2—O6	1.505 (5)	O11—Eu <sup>x</sup>	2.355 (5)
O11 <sup>i</sup> —Eu—O12	146.43 (17)	O12—Ag—Eu	40.66 (10)
O11 <sup>i</sup> —Eu—O9 <sup>ii</sup>	137.70 (16)	O6 <sup>iii</sup> —Ag—Eu	117.27 (12)
O12—Eu—O9 <sup>ii</sup>	74.62 (16)	O1—Ag—Eu	119.92 (10)
O11 <sup>i</sup> —Eu—O5 <sup>ii</sup>	85.21 (16)	O8 <sup>i</sup> —Ag—Eu <sup>v</sup>	142.17 (11)
O12—Eu—O5 <sup>ii</sup>	69.01 (16)	O12—Ag—Eu <sup>v</sup>	114.81 (10)
O9 <sup>ii</sup> —Eu—O5 <sup>ii</sup>	114.34 (16)	O6 <sup>iii</sup> —Ag—Eu <sup>v</sup>	39.40 (11)
O11 <sup>i</sup> —Eu—O1 <sup>iii</sup>	108.89 (17)	O1—Ag—Eu <sup>v</sup>	85.49 (10)
O12—Eu—O1 <sup>iii</sup>	77.74 (15)	Eu—Ag—Eu <sup>v</sup>	152.34 (2)
O9 <sup>ii</sup> —Eu—O1 <sup>iii</sup>	84.55 (16)	O1—P1—O2	116.6 (3)
O5 <sup>ii</sup> —Eu—O1 <sup>iii</sup>	134.29 (16)	O1—P1—O3	108.0 (3)
O11 <sup>i</sup> —Eu—O6 <sup>iv</sup>	70.99 (18)	O2—P1—O3	111.5 (3)
O12—Eu—O6 <sup>iv</sup>	140.07 (18)	O1—P1—O4	107.3 (3)
O9 <sup>ii</sup> —Eu—O6 <sup>iv</sup>	74.93 (16)	O2—P1—O4	113.3 (3)
O5 <sup>ii</sup> —Eu—O6 <sup>iv</sup>	148.82 (17)	O3—P1—O4	98.4 (3)
O1 <sup>iii</sup> —Eu—O6 <sup>iv</sup>	74.24 (16)	O5—P2—O6	120.1 (3)
O11 <sup>i</sup> —Eu—O2 <sup>ii</sup>	70.26 (16)	O5—P2—O4	109.1 (3)
O12—Eu—O2 <sup>ii</sup>	117.94 (15)	O6—P2—O4	104.9 (3)
O9 <sup>ii</sup> —Eu—O2 <sup>ii</sup>	80.70 (17)	O5—P2—O7 <sup>vi</sup>	111.5 (3)
O5 <sup>ii</sup> —Eu—O2 <sup>ii</sup>	71.45 (17)	O6—P2—O7 <sup>vi</sup>	106.6 (3)
O1 <sup>iii</sup> —Eu—O2 <sup>ii</sup>	154.17 (16)	O4—P2—O7 <sup>vi</sup>	103.2 (3)
O6 <sup>iv</sup> —Eu—O2 <sup>ii</sup>	81.49 (16)	O8—P3—O9	120.0 (3)
O11 <sup>i</sup> —Eu—O8 <sup>i</sup>	68.78 (16)	O8—P3—O10	111.3 (3)
O12—Eu—O8 <sup>i</sup>	82.12 (15)	O9—P3—O10	106.8 (3)
O9 <sup>ii</sup> —Eu—O8 <sup>i</sup>	151.72 (16)	O8—P3—O7	105.3 (3)
O5 <sup>ii</sup> —Eu—O8 <sup>i</sup>	70.38 (16)	O9—P3—O7	110.4 (3)
O1 <sup>iii</sup> —Eu—O8 <sup>i</sup>	74.87 (16)	O10—P3—O7	101.6 (3)
O6 <sup>iv</sup> —Eu—O8 <sup>i</sup>	116.40 (15)	O11—P4—O12	117.5 (3)
O2 <sup>ii</sup> —Eu—O8 <sup>i</sup>	125.20 (17)	O11—P4—O3 <sup>vii</sup>	105.7 (3)
O11 <sup>i</sup> —Eu—Ag	103.74 (12)	O12—P4—O3 <sup>vii</sup>	112.8 (3)
O12—Eu—Ag	43.03 (12)	O11—P4—O10	111.0 (3)
O9 <sup>ii</sup> —Eu—Ag	117.57 (11)	O12—P4—O10	106.1 (3)
O5 <sup>ii</sup> —Eu—Ag	49.41 (11)	O3 <sup>vii</sup> —P4—O10	102.9 (3)
O1 <sup>iii</sup> —Eu—Ag	84.88 (11)	P1—O1—Eu <sup>viii</sup>	144.5 (3)
O6 <sup>iv</sup> —Eu—Ag	154.81 (10)	P1—O1—Ag	93.9 (3)
O2 <sup>ii</sup> —Eu—Ag	120.77 (12)	Eu <sup>viii</sup> —O1—Ag	112.98 (17)

O8 <sup>i</sup> —Eu—Ag	42.51 (10)	P1—O2—Eu <sup>v</sup>	128.1 (3)
O11 <sup>i</sup> —Eu—Ag <sup>ii</sup>	52.44 (12)	P1—O3—P4 <sup>vii</sup>	137.7 (4)
O12—Eu—Ag <sup>ii</sup>	155.75 (11)	P2—O4—P1	133.6 (3)
O9 <sup>ii</sup> —Eu—Ag <sup>ii</sup>	85.32 (11)	P2—O5—Eu <sup>v</sup>	133.2 (3)
O5 <sup>ii</sup> —Eu—Ag <sup>ii</sup>	108.69 (11)	P2—O6—Eu <sup>ix</sup>	142.4 (3)
O1 <sup>iii</sup> —Eu—Ag <sup>ii</sup>	114.28 (11)	P2—O6—Ag <sup>viii</sup>	115.3 (2)
O6 <sup>iv</sup> —Eu—Ag <sup>ii</sup>	40.55 (12)	Eu <sup>ix</sup> —O6—Ag <sup>viii</sup>	100.06 (18)
O2 <sup>ii</sup> —Eu—Ag <sup>ii</sup>	43.64 (11)	P2 <sup>vi</sup> —O7—P3	131.3 (3)
O8 <sup>i</sup> —Eu—Ag <sup>ii</sup>	120.64 (11)	P3—O8—Ag <sup>x</sup>	108.8 (3)
Ag—Eu—Ag <sup>ii</sup>	152.34 (2)	P3—O8—Eu <sup>x</sup>	145.5 (3)
O8 <sup>i</sup> —Ag—O12	80.67 (15)	Ag <sup>x</sup> —O8—Eu <sup>x</sup>	94.16 (15)
O8 <sup>i</sup> —Ag—O6 <sup>iii</sup>	109.46 (15)	P3—O9—Eu <sup>v</sup>	140.7 (3)
O12—Ag—O6 <sup>iii</sup>	93.64 (16)	P3—O10—P4	130.2 (3)
O8 <sup>i</sup> —Ag—O1	110.19 (16)	P4—O11—Eu <sup>x</sup>	150.8 (3)
O12—Ag—O1	132.06 (14)	P4—O12—Eu	137.3 (3)
O6 <sup>iii</sup> —Ag—O1	122.79 (16)	P4—O12—Ag	118.8 (2)
O8 <sup>i</sup> —Ag—Eu	43.33 (11)	Eu—O12—Ag	96.31 (16)

Symmetry codes: (i)  $x-1/2, -y+3/2, z-1/2$ ; (ii)  $x, y, z-1$ ; (iii)  $x+1/2, -y+3/2, z-1/2$ ; (iv)  $x+1/2, -y+3/2, z-3/2$ ; (v)  $x, y, z+1$ ; (vi)  $-x+1, -y+2, -z+3$ ; (vii)  $-x+1, -y+2, -z+2$ ; (viii)  $x-1/2, -y+3/2, z+1/2$ ; (ix)  $x-1/2, -y+3/2, z+3/2$ ; (x)  $x+1/2, -y+3/2, z+1/2$ .