

Poly[bis(4,4'-bipyridine)(μ_3 -4,4'-dicarboxybiphenyl-3,3'-dicarboxylato)iron(II)]

Qun-Hui Meng,^a Hui-Ling Lai,^a Han Lu,^a Yi-Fan Luo^{a*} and Rong-Hua Zeng^{a,b}

^aSchool of Chemistry and Environment, South China Normal University, Guangzhou 510006, People's Republic of China, and ^bSouth China Normal University, Key Laboratory of Technology of Electrochemical Energy Storage and Power Generation, in Guangdong Universities, Guangzhou 510006, People's Republic of China
Correspondence e-mail: luoyf2004@yahoo.com.cn


Received 25 October 2009; accepted 3 November 2009

Key indicators: single-crystal X-ray study; $T = 296$ K; mean $\sigma(\text{C}-\text{C}) = 0.003$ Å; R factor = 0.037; wR factor = 0.100; data-to-parameter ratio = 12.1.

In the polymeric title complex, $[\text{Fe}(\text{C}_{16}\text{H}_8\text{O}_8)(\text{C}_{10}\text{H}_8\text{N}_2)_2]_n$, the iron(II) cation is coordinated by four O atoms from three different 4,4'-dicarboxybiphenyl-3,3'-dicarboxylate ligands and two N atoms from two 4,4'-bipyridine ligands in a distorted octahedral geometry. The 4,4'-dicarboxybiphenyl-3,3'-dicarboxylate ligands bridge adjacent cations, forming chains parallel to the c axis. The chains are further connected by intermolecular $\text{O}-\text{H}\cdots\text{N}$ hydrogen bonds, forming two-dimensional supramolecular layers parallel to (010).

Related literature

For general background to self-assembling coordination polymers, see: Li *et al.* (2008); Yaghi *et al.* (2003). For related structures, see: Li *et al.* (2009); Liu *et al.* (2009); Wang *et al.* (2007).



Experimental

Crystal data

$[\text{Fe}(\text{C}_{16}\text{H}_8\text{O}_8)(\text{C}_{10}\text{H}_8\text{N}_2)_2]$
 $M_r = 696.44$
 Monoclinic, $P2_1/c$
 $a = 11.9569$ (13) Å
 $b = 24.114$ (3) Å
 $c = 10.7232$ (12) Å
 $\beta = 105.855$ (1)°

$V = 2974.2$ (6) Å³
 $Z = 4$
 Mo $K\alpha$ radiation
 $\mu = 0.57$ mm⁻¹
 $T = 296$ K
 $0.23 \times 0.21 \times 0.19$ mm

Data collection

Bruker APEXII area-detector diffractometer
 Absorption correction: multi-scan (SADABS; Bruker, 2005)
 $T_{\min} = 0.880$, $T_{\max} = 0.899$

15189 measured reflections
 5363 independent reflections
 4293 reflections with $I > 2\sigma(I)$
 $R_{\text{int}} = 0.038$

Refinement

$R[F^2 > 2\sigma(F^2)] = 0.037$
 $wR(F^2) = 0.100$
 $S = 1.03$
 5363 reflections

444 parameters
 H-atom parameters constrained
 $\Delta\rho_{\max} = 0.71$ e Å⁻³
 $\Delta\rho_{\min} = -0.46$ e Å⁻³

Table 1

Hydrogen-bond geometry (Å, °).

$D-\text{H}\cdots A$	$D-\text{H}$	$\text{H}\cdots A$	$D\cdots A$	$D-\text{H}\cdots A$
$\text{O5}-\text{H5}\cdots\text{N2}^i$	0.82	1.86	2.677 (2)	171
$\text{O3}-\text{H3}\cdots\text{N4}^{ii}$	0.82	1.81	2.598 (3)	162

Symmetry codes: (i) $x - 1, y, z - 2$; (ii) $x + 1, y, z + 1$.

Data collection: APEX2 (Bruker, 2005); cell refinement: SAINT (Bruker, 2005); data reduction: SAINT; program(s) used to solve structure: SHELXS97 (Sheldrick, 2008); program(s) used to refine structure: SHELXL97 (Sheldrick, 2008); molecular graphics: SHELXTL (Sheldrick, 2008); software used to prepare material for publication: SHELXTL.

The authors acknowledge the Chan Xue Yan Cooperative Special Project of Guangdong Province and the Ministry of Science and Technology of PRC (No. 2007A090302046), the Project of Science and Technology of Guangdong Province (No. 2007A020200002-4) and the Natural Science Foundation of Guangdong Province (No. 9151063101000037) for supporting this work.

Supplementary data and figures for this paper are available from the IUCr electronic archives (Reference: RZ2381).

References

- Bruker (2005). *APEX2*, *SAINT* and *SADABS*. Bruker AXS Inc., Madison, Wisconsin, USA.
- Li, C.-P., Tian, Y.-L. & Guo, Y.-M. (2008). *Inorg. Chem. Commun.* **11**, 1405–1408.
- Li, F., Wang, W.-W., Ji, X., Cao, C.-C. & Zhu, D.-Y. (2009). *Acta Cryst.* **E65**, o244.
- Liu, G.-X., Zhu, K., Chen, H., Huang, R.-Y. & Ren, X.-M. (2009). *Z. Anorg. Allg. Chem.* **635**, 156–164.
- Sheldrick, G. M. (2008). *Acta Cryst.* **A64**, 112–122.
- Wang, J.-J., Yang, M.-L. & Hu, H.-M. (2007). *Z. Anorg. Allg. Chem.* **633**, 341–345.
- Yaghi, O. M., O’Keeffe, M., Ockwig, N. W., Chae, H. K., Eddaoudi, M. & Kim, J. (2003). *Nature* (London), **423**, 705–714.

supporting information

Acta Cryst. (2009). E65, m1537–m1538 [doi:10.1107/S1600536809046273]

Poly[bis(4,4'-bipyridine)(μ_3 -4,4'-dicarboxybiphenyl-3,3'-dicarboxylato)iron(II)]**Qun-Hui Meng, Hui-Ling Lai, Han Lu, Yi-Fan Luo and Rong-Hua Zeng****S1. Comment**

The construction of self-assembling coordination polymers is of current interest in the fields of supramolecular chemistry and crystal engineering, because of their potential applications in gas storage, molecular sieves, ion exchange, catalysis, magnetism, nonlinearoptics, and molecular sensing (Li *et al.*, 2008; Yaghi *et al.*, 2003). Due to the presence of four carboxylic groups, 4,4'-dicarboxybiphenyl-3,3'-dicarboxylate ligands are promising building blocks for the construction of novel metal-organic coordination polymers (Li *et al.*, 2009; Liu *et al.*, 2009; Wang *et al.*, 2007). Herein, we report the title new metal-organic framework, which was synthesized under hydrothermal conditions.


In the title complex (Fig. 1), each iron(II) atom exhibits a distorted octahedral geometry, defined by four oxygen atoms from three different 4,4'-dicarboxybiphenyl-3,3'-dicarboxylate ligands and two nitrogen atoms from two different 4,4'-bipyridine ligands. The Fe—O and Fe—N distances range from 2.0244 (1) to 2.3327 (1) Å and 2.2201 (1) to 2.2615 (1) Å, respectively, while the O—Fe—O angles and N—Fe—O angles fall in the range from 58.64 (6) to 160.43 (7) °A and 82.29 (6) to 102.91 (7) °A, respectively. The dihedral angles between the N1/C1—C5 and N2/C6—C10, N3/C11—C15 and N4/C16—C20, C22/C23/C25—c28 and C29—C32/C33/C34 are 25.74 (8), 26.91 (9) and 37.39 (7)°, respectively. Adjacent metal centres are connected by the 4,4'-dicarboxybiphenyl-3,3'-dicarboxylate ligands to form chains (Fig. 2) running parallel to the *c* axis. Intermolecular O—H...N hydrogen bonds (Table 1) link the chains into two-dimensional supramolecular layers parallel to (0 1 0) (Fig. 3).

S2. Experimental


A mixture of FeSO₄·7H₂O (0.139 g, 0.5mmol), 4,4'-bipyridine (0.078 g; 0.5 mmol), biphenyl-3,3',-4,4'-tetracarboxylic acid (0.165 g; 0.5 mmol), water (10mL) were stirred vigorously for 30 min and then sealed in a Teflon-lined stainless-steel autoclave (25 mL capacity). The autoclave was heated and maintained at 423K for 3 days, then cooled to room temperature at 5K h⁻¹. Red block crystals suitable for X-ray analysis were obtained.

S3. Refinement


Carboxy H atoms were located in a difference Fourier map and refined using a riding model approximation, with O—H = 0.82 Å and with 1.5 *U*_{eq}(O). All other H atoms were placed at calculated positions and treated as riding on parent atoms with C—H = 0.93 Å, and with *U*_{iso}(H) = 1.2 *U*_{eq}(C).

**Figure 1**

The molecular structure of the title compound showing the atomic-numbering scheme. Displacement ellipsoids drawn at the 30% probability level. H atoms are omitted for clarity. [Symmetry codes: (#1) $x, y, 1+z$; (#2) $1-x, 2-y, 1-z$]

**Figure 2**

Partial crystal packing of the title compound showing a one-dimensional chain running parallel to the c axis. 4,4'-Bi-pyridine ligands are omitted for clarity.

**Figure 3**

Partial crystal packing of the title compound showing the two-dimensional supramolecular layers parallel to (0 1 0). Hydrogen bonds are shown as dashed lines.

Poly[bis(4,4'-bipyridine)(μ_3 -4,4'-dicarboxybiphenyl-3,3'-dicarboxylato)iron(II)]

Crystal data

[Fe(C₁₆H₈O₈)(C₁₀H₈N₂)₂]

$M_r = 696.44$

Monoclinic, $P2_1/c$

Hall symbol: -P 2ybc

$a = 11.9569$ (13) Å

$b = 24.114$ (3) Å

$c = 10.7232$ (12) Å

$\beta = 105.855$ (1)°

$V = 2974.2$ (6) Å³

$Z = 4$

$F(000) = 1432$

$D_x = 1.555$ Mg m⁻³

Mo $K\alpha$ radiation, $\lambda = 0.71073$ Å

Cell parameters from 4905 reflections

$\theta = 2.4$ – 27.0 °

$\mu = 0.57$ mm⁻¹

$T = 296$ K

Block, red

$0.23 \times 0.21 \times 0.19$ mm

Data collection

Bruker APEXII area-detector diffractometer	15189 measured reflections 5363 independent reflections
Radiation source: fine-focus sealed tube	4293 reflections with $I > 2\sigma(I)$
Graphite monochromator	$R_{\text{int}} = 0.038$
φ and ω scans	$\theta_{\text{max}} = 25.2^\circ$, $\theta_{\text{min}} = 1.7^\circ$
Absorption correction: multi-scan (<i>SADABS</i> ; Bruker, 2005)	$h = -14 \rightarrow 10$ $k = -28 \rightarrow 26$ $l = -12 \rightarrow 12$
$T_{\text{min}} = 0.880$, $T_{\text{max}} = 0.899$	

Refinement

Refinement on F^2	Secondary atom site location: difference Fourier map
Least-squares matrix: full	Hydrogen site location: inferred from neighbouring sites
$R[F^2 > 2\sigma(F^2)] = 0.037$	H-atom parameters constrained
$wR(F^2) = 0.100$	$w = 1/[\sigma^2(F_o^2) + (0.0462P)^2 + 1.5067P]$
$S = 1.03$	where $P = (F_o^2 + 2F_c^2)/3$
5363 reflections	$(\Delta/\sigma)_{\text{max}} = 0.002$
444 parameters	$\Delta\rho_{\text{max}} = 0.71 \text{ e } \text{\AA}^{-3}$
0 restraints	$\Delta\rho_{\text{min}} = -0.46 \text{ e } \text{\AA}^{-3}$
Primary atom site location: structure-invariant direct methods	

Special details

Geometry. All esds (except the esd in the dihedral angle between two l.s. planes) are estimated using the full covariance matrix. The cell esds are taken into account individually in the estimation of esds in distances, angles and torsion angles; correlations between esds in cell parameters are only used when they are defined by crystal symmetry. An approximate (isotropic) treatment of cell esds is used for estimating esds involving l.s. planes.

Refinement. Refinement of F^2 against ALL reflections. The weighted R-factor wR and goodness of fit S are based on F^2 , conventional R-factors R are based on F , with F set to zero for negative F^2 . The threshold expression of $F^2 > 2\sigma(F^2)$ is used only for calculating R-factors(gt) etc. and is not relevant to the choice of reflections for refinement. R-factors based on F^2 are statistically about twice as large as those based on F , and R-factors based on ALL data will be even larger.

Fractional atomic coordinates and isotropic or equivalent isotropic displacement parameters (\AA^2)

	<i>x</i>	<i>y</i>	<i>z</i>	$U_{\text{iso}}^*/U_{\text{eq}}$
Fe1	0.58299 (3)	0.948957 (13)	0.88381 (3)	0.02617 (11)
C27	0.63026 (19)	0.80826 (9)	0.4436 (2)	0.0267 (5)
C11	0.4184 (2)	0.97360 (10)	0.5952 (2)	0.0331 (6)
H11	0.4542	1.0082	0.6064	0.040*
O3	0.88485 (15)	0.84329 (7)	0.88903 (16)	0.0417 (4)
H3	0.9409	0.8416	0.9532	0.063*
C29	0.5469 (2)	0.81316 (9)	0.3128 (2)	0.0277 (5)
N2	1.05946 (18)	0.88387 (10)	1.71537 (19)	0.0416 (5)
C3	0.8429 (2)	0.91461 (10)	1.3316 (2)	0.0322 (5)
O5	0.23281 (15)	0.87426 (7)	-0.06664 (16)	0.0414 (4)
H5	0.1792	0.8734	-0.1333	0.062*
C21	0.6846 (2)	0.88567 (9)	0.7580 (2)	0.0279 (5)
N1	0.70900 (17)	0.93693 (8)	1.07668 (18)	0.0327 (5)
N4	0.0513 (2)	0.85951 (11)	0.0994 (2)	0.0510 (6)
N3	0.44003 (17)	0.93946 (8)	0.69706 (18)	0.0304 (4)
C10	0.9865 (2)	0.85667 (11)	1.4936 (2)	0.0382 (6)

H10	0.9875	0.8309	1.4293	0.046*
C5	0.7413 (2)	0.88541 (11)	1.1179 (2)	0.0388 (6)
H5A	0.7179	0.8564	1.0593	0.047*
C2	0.8088 (2)	0.96780 (11)	1.2899 (2)	0.0435 (7)
H2	0.8296	0.9974	1.3471	0.052*
C6	0.9155 (2)	0.90314 (11)	1.4651 (2)	0.0332 (5)
C1	0.7440 (2)	0.97724 (11)	1.1640 (2)	0.0432 (7)
H1	0.7237	1.0136	1.1386	0.052*
C4	0.8068 (2)	0.87257 (11)	1.2414 (2)	0.0383 (6)
H4	0.8266	0.8359	1.2642	0.046*
C9	1.0557 (2)	0.84914 (12)	1.6183 (2)	0.0414 (6)
H9	1.1026	0.8177	1.6355	0.050*
C7	0.9158 (2)	0.93795 (12)	1.5675 (3)	0.0482 (7)
H7	0.8675	0.9689	1.5544	0.058*
C8	0.9880 (3)	0.92674 (13)	1.6896 (2)	0.0506 (7)
H8	0.9861	0.9506	1.7571	0.061*
C12	0.3463 (2)	0.96087 (10)	0.4744 (2)	0.0338 (6)
H12	0.3344	0.9864	0.4069	0.041*
C16	0.2130 (2)	0.89236 (11)	0.3283 (2)	0.0350 (6)
C14	0.3124 (2)	0.87458 (10)	0.5620 (2)	0.0358 (6)
H14	0.2764	0.8401	0.5547	0.043*
C17	0.1517 (3)	0.93092 (12)	0.2401 (3)	0.0519 (8)
H17	0.1640	0.9687	0.2559	0.062*
C13	0.2917 (2)	0.90935 (10)	0.4548 (2)	0.0313 (5)
C15	0.3853 (2)	0.89073 (10)	0.6785 (2)	0.0345 (6)
H15	0.3973	0.8664	0.7482	0.041*
C20	0.1939 (2)	0.83734 (12)	0.2949 (3)	0.0484 (7)
H20	0.2353	0.8100	0.3495	0.058*
C19	0.1136 (3)	0.82278 (13)	0.1808 (3)	0.0527 (8)
H19	0.1027	0.7854	0.1601	0.063*
C18	0.0727 (3)	0.91279 (14)	0.1290 (3)	0.0622 (9)
H18	0.0318	0.9392	0.0712	0.075*
C26	0.7131 (2)	0.76653 (10)	0.4723 (2)	0.0313 (5)
H26	0.7138	0.7393	0.4112	0.038*
C36	0.51638 (19)	0.86533 (9)	0.2589 (2)	0.0269 (5)
H36	0.5478	0.8966	0.3066	0.032*
C22	0.70735 (19)	0.84500 (9)	0.66113 (19)	0.0246 (5)
C25	0.7947 (2)	0.76543 (10)	0.5919 (2)	0.0305 (5)
H25	0.8516	0.7380	0.6087	0.037*
C34	0.44068 (19)	0.87230 (9)	0.1366 (2)	0.0250 (5)
C23	0.79408 (19)	0.80409 (9)	0.6875 (2)	0.0258 (5)
C33	0.2957 (2)	0.82910 (10)	−0.0585 (2)	0.0344 (6)
C28	0.62884 (19)	0.84684 (9)	0.5393 (2)	0.0284 (5)
H28	0.5733	0.8749	0.5210	0.034*
C30	0.5005 (2)	0.76689 (10)	0.2393 (2)	0.0394 (6)
H30	0.5216	0.7315	0.2717	0.047*
C24	0.8873 (2)	0.80139 (10)	0.8127 (2)	0.0296 (5)
C32	0.3894 (2)	0.82577 (10)	0.0668 (2)	0.0310 (5)

C31	0.4231 (2)	0.77351 (10)	0.1183 (2)	0.0415 (7)
H31	0.3929	0.7422	0.0700	0.050*
O2	0.62783 (14)	0.86750 (7)	0.83378 (14)	0.0317 (4)
O1	0.70685 (16)	0.93579 (7)	0.75185 (16)	0.0382 (4)
O4	0.95713 (16)	0.76380 (8)	0.83860 (17)	0.0479 (5)
O6	0.27834 (18)	0.79341 (8)	-0.14063 (18)	0.0575 (6)
C35	0.43099 (19)	0.92924 (9)	0.0796 (2)	0.0256 (5)
O7	0.45273 (14)	0.93505 (7)	-0.02766 (14)	0.0338 (4)
O8	0.40781 (15)	0.96848 (7)	0.14606 (15)	0.0355 (4)

Atomic displacement parameters (Å²)

	U^{11}	U^{22}	U^{33}	U^{12}	U^{13}	U^{23}
Fe1	0.0328 (2)	0.02408 (19)	0.01910 (18)	0.00295 (13)	0.00281 (13)	-0.00112 (12)
C27	0.0317 (13)	0.0253 (12)	0.0203 (11)	0.0002 (9)	0.0025 (10)	0.0004 (9)
C11	0.0381 (14)	0.0307 (13)	0.0265 (12)	-0.0020 (10)	0.0023 (10)	-0.0001 (10)
O3	0.0371 (11)	0.0483 (11)	0.0302 (9)	0.0044 (8)	-0.0070 (7)	-0.0103 (8)
C29	0.0330 (13)	0.0271 (12)	0.0209 (11)	0.0031 (10)	0.0036 (10)	0.0012 (9)
N2	0.0345 (12)	0.0527 (14)	0.0309 (12)	-0.0021 (10)	-0.0023 (9)	0.0060 (10)
C3	0.0269 (13)	0.0415 (15)	0.0247 (12)	0.0026 (10)	0.0010 (10)	-0.0004 (10)
O5	0.0370 (11)	0.0463 (11)	0.0307 (10)	0.0071 (8)	-0.0083 (8)	-0.0022 (8)
C21	0.0298 (13)	0.0275 (13)	0.0208 (11)	0.0054 (10)	-0.0024 (9)	-0.0008 (9)
N1	0.0348 (12)	0.0340 (12)	0.0251 (10)	0.0045 (9)	0.0012 (9)	-0.0007 (8)
N4	0.0408 (14)	0.0683 (18)	0.0352 (13)	-0.0011 (12)	-0.0041 (10)	-0.0144 (12)
N3	0.0311 (11)	0.0349 (12)	0.0235 (10)	0.0017 (8)	0.0047 (8)	-0.0001 (8)
C10	0.0369 (15)	0.0401 (15)	0.0328 (13)	0.0020 (11)	0.0014 (11)	0.0013 (11)
C5	0.0485 (16)	0.0371 (14)	0.0241 (12)	0.0025 (12)	-0.0013 (11)	-0.0029 (10)
C2	0.0490 (17)	0.0376 (15)	0.0335 (14)	0.0063 (12)	-0.0065 (12)	-0.0082 (11)
C6	0.0270 (13)	0.0425 (15)	0.0263 (12)	-0.0008 (10)	0.0008 (10)	0.0018 (10)
C1	0.0532 (17)	0.0352 (15)	0.0307 (14)	0.0117 (12)	-0.0062 (12)	0.0001 (11)
C4	0.0473 (16)	0.0349 (14)	0.0259 (12)	0.0050 (11)	-0.0013 (11)	0.0028 (10)
C9	0.0344 (15)	0.0457 (16)	0.0385 (15)	0.0047 (12)	0.0004 (11)	0.0098 (12)
C7	0.0495 (18)	0.0548 (18)	0.0308 (14)	0.0195 (13)	-0.0051 (12)	-0.0021 (12)
C8	0.0538 (18)	0.0607 (19)	0.0289 (14)	0.0114 (15)	-0.0031 (12)	-0.0048 (13)
C12	0.0372 (14)	0.0360 (14)	0.0239 (12)	-0.0020 (11)	0.0013 (10)	0.0044 (10)
C16	0.0298 (13)	0.0428 (15)	0.0279 (12)	-0.0010 (11)	0.0004 (10)	-0.0044 (11)
C14	0.0337 (14)	0.0323 (14)	0.0370 (14)	-0.0048 (10)	0.0020 (11)	0.0009 (11)
C17	0.0584 (19)	0.0431 (17)	0.0396 (16)	0.0095 (14)	-0.0115 (13)	-0.0097 (13)
C13	0.0262 (13)	0.0370 (14)	0.0273 (12)	0.0026 (10)	0.0015 (10)	-0.0040 (10)
C15	0.0354 (14)	0.0371 (14)	0.0283 (12)	-0.0022 (11)	0.0042 (10)	0.0060 (10)
C20	0.0502 (17)	0.0414 (16)	0.0422 (16)	-0.0034 (13)	-0.0067 (13)	-0.0029 (12)
C19	0.0542 (19)	0.0511 (18)	0.0448 (16)	-0.0116 (14)	0.0000 (14)	-0.0133 (14)
C18	0.062 (2)	0.065 (2)	0.0414 (17)	0.0152 (16)	-0.0162 (15)	-0.0066 (15)
C26	0.0390 (14)	0.0292 (13)	0.0233 (11)	0.0060 (10)	0.0048 (10)	-0.0049 (9)
C36	0.0336 (13)	0.0241 (12)	0.0200 (11)	0.0001 (9)	0.0022 (9)	-0.0040 (9)
C22	0.0300 (12)	0.0233 (12)	0.0196 (11)	-0.0002 (9)	0.0050 (9)	0.0009 (8)
C25	0.0345 (13)	0.0278 (12)	0.0271 (12)	0.0094 (10)	0.0048 (10)	0.0008 (9)
C34	0.0285 (12)	0.0258 (12)	0.0188 (11)	0.0029 (9)	0.0034 (9)	-0.0006 (9)

C23	0.0272 (12)	0.0263 (12)	0.0220 (11)	-0.0011 (9)	0.0036 (9)	0.0024 (9)
C33	0.0363 (14)	0.0338 (14)	0.0274 (12)	-0.0049 (11)	-0.0011 (10)	0.0018 (10)
C28	0.0304 (13)	0.0272 (12)	0.0247 (11)	0.0076 (9)	0.0027 (10)	0.0015 (9)
C30	0.0529 (17)	0.0250 (13)	0.0306 (13)	0.0028 (11)	-0.0049 (11)	0.0022 (10)
C24	0.0286 (13)	0.0348 (14)	0.0235 (11)	-0.0014 (10)	0.0039 (10)	0.0030 (10)
C32	0.0354 (13)	0.0296 (13)	0.0237 (11)	-0.0011 (10)	0.0011 (10)	-0.0013 (10)
C31	0.0551 (18)	0.0253 (13)	0.0331 (14)	-0.0048 (11)	-0.0068 (12)	-0.0038 (10)
O2	0.0383 (10)	0.0346 (9)	0.0204 (8)	0.0044 (7)	0.0049 (7)	-0.0013 (7)
O1	0.0517 (11)	0.0256 (9)	0.0346 (9)	0.0016 (8)	0.0076 (8)	-0.0032 (7)
O4	0.0446 (11)	0.0457 (12)	0.0422 (11)	0.0147 (9)	-0.0071 (8)	0.0026 (9)
O6	0.0701 (14)	0.0466 (12)	0.0369 (11)	0.0030 (10)	-0.0176 (9)	-0.0143 (9)
C35	0.0243 (12)	0.0267 (12)	0.0210 (11)	-0.0005 (9)	-0.0017 (9)	-0.0005 (9)
O7	0.0377 (10)	0.0395 (10)	0.0233 (8)	0.0002 (7)	0.0068 (7)	0.0056 (7)
O8	0.0532 (11)	0.0234 (9)	0.0284 (9)	0.0038 (7)	0.0084 (8)	-0.0023 (7)

Geometric parameters (Å, °)

Fe1—O8 ⁱ	2.0244 (17)	C7—C8	1.384 (4)
Fe1—O7 ⁱⁱ	2.0609 (16)	C7—H7	0.9300
Fe1—O2	2.1426 (16)	C8—H8	0.9300
Fe1—N1	2.2201 (19)	C12—C13	1.392 (3)
Fe1—N3	2.2615 (19)	C12—H12	0.9300
Fe1—O1	2.3327 (18)	C16—C20	1.377 (4)
C27—C26	1.387 (3)	C16—C17	1.384 (4)
C27—C28	1.389 (3)	C16—C13	1.482 (3)
C27—C29	1.487 (3)	C14—C15	1.370 (3)
C11—N3	1.335 (3)	C14—C13	1.390 (3)
C11—C12	1.381 (3)	C14—H14	0.9300
C11—H11	0.9300	C17—C18	1.374 (4)
O3—C24	1.306 (3)	C17—H17	0.9300
O3—H3	0.8200	C15—H15	0.9300
C29—C36	1.391 (3)	C20—C19	1.379 (4)
C29—C30	1.391 (3)	C20—H20	0.9300
N2—C8	1.321 (4)	C19—H19	0.9300
N2—C9	1.327 (3)	C18—H18	0.9300
C3—C2	1.383 (4)	C26—C25	1.383 (3)
C3—C4	1.386 (3)	C26—H26	0.9300
C3—C6	1.483 (3)	C36—C34	1.385 (3)
O5—C33	1.313 (3)	C36—H36	0.9300
O5—H5	0.8200	C22—C28	1.386 (3)
C21—O1	1.243 (3)	C22—C23	1.403 (3)
C21—O2	1.271 (3)	C25—C23	1.387 (3)
C21—C22	1.506 (3)	C25—H25	0.9300
N1—C1	1.335 (3)	C34—C32	1.395 (3)
N1—C5	1.339 (3)	C34—C35	1.495 (3)
N4—C19	1.321 (4)	C23—C24	1.494 (3)
N4—C18	1.331 (4)	C33—O6	1.208 (3)
N3—C15	1.333 (3)	C33—C32	1.498 (3)

C10—C9	1.379 (3)	C28—H28	0.9300
C10—C6	1.389 (3)	C30—C31	1.382 (3)
C10—H10	0.9300	C30—H30	0.9300
C5—C4	1.378 (3)	C24—O4	1.212 (3)
C5—H5A	0.9300	C32—C31	1.391 (3)
C2—C1	1.380 (3)	C31—H31	0.9300
C2—H2	0.9300	C35—O7	1.254 (3)
C6—C7	1.382 (4)	C35—O8	1.260 (3)
C1—H1	0.9300	O7—Fe1 ⁱⁱⁱ	2.0609 (16)
C4—H4	0.9300	O8—Fe1 ⁱ	2.0244 (17)
C9—H9	0.9300		
O8 ⁱ —Fe1—O7 ⁱⁱ	108.27 (7)	C13—C12—H12	120.4
O8 ⁱ —Fe1—O2	146.50 (7)	C20—C16—C17	116.8 (2)
O7 ⁱⁱ —Fe1—O2	103.80 (7)	C20—C16—C13	121.5 (2)
O8 ⁱ —Fe1—N1	102.91 (7)	C17—C16—C13	121.6 (2)
O7 ⁱⁱ —Fe1—N1	87.46 (7)	C15—C14—C13	120.5 (2)
O2—Fe1—N1	87.76 (7)	C15—C14—H14	119.7
O8 ⁱ —Fe1—N3	91.15 (7)	C13—C14—H14	119.7
O7 ⁱⁱ —Fe1—N3	84.72 (7)	C18—C17—C16	119.2 (3)
O2—Fe1—N3	82.29 (6)	C18—C17—H17	120.4
N1—Fe1—N3	165.49 (8)	C16—C17—H17	120.4
O8 ⁱ —Fe1—O1	88.10 (6)	C14—C13—C12	116.3 (2)
O7 ⁱⁱ —Fe1—O1	160.43 (7)	C14—C13—C16	121.0 (2)
O2—Fe1—O1	58.64 (6)	C12—C13—C16	122.6 (2)
N1—Fe1—O1	99.53 (7)	N3—C15—C14	123.4 (2)
N3—Fe1—O1	84.29 (7)	N3—C15—H15	118.3
C26—C27—C28	118.3 (2)	C14—C15—H15	118.3
C26—C27—C29	121.45 (19)	C16—C20—C19	120.1 (3)
C28—C27—C29	120.2 (2)	C16—C20—H20	120.0
N3—C11—C12	124.2 (2)	C19—C20—H20	120.0
N3—C11—H11	117.9	N4—C19—C20	123.1 (3)
C12—C11—H11	117.9	N4—C19—H19	118.5
C24—O3—H3	109.5	C20—C19—H19	118.5
C36—C29—C30	118.1 (2)	N4—C18—C17	123.7 (3)
C36—C29—C27	119.7 (2)	N4—C18—H18	118.1
C30—C29—C27	122.1 (2)	C17—C18—H18	118.1
C8—N2—C9	116.6 (2)	C25—C26—C27	120.0 (2)
C2—C3—C4	116.4 (2)	C25—C26—H26	120.0
C2—C3—C6	121.9 (2)	C27—C26—H26	120.0
C4—C3—C6	121.7 (2)	C34—C36—C29	122.2 (2)
C33—O5—H5	109.5	C34—C36—H36	118.9
O1—C21—O2	121.9 (2)	C29—C36—H36	118.9
O1—C21—C22	121.0 (2)	C28—C22—C23	119.0 (2)
O2—C21—C22	116.4 (2)	C28—C22—C21	115.20 (19)
C1—N1—C5	115.9 (2)	C23—C22—C21	125.58 (19)
C1—N1—Fe1	124.13 (16)	C26—C25—C23	121.8 (2)
C5—N1—Fe1	119.29 (16)	C26—C25—H25	119.1

C19—N4—C18	116.9 (2)	C23—C25—H25	119.1
C15—N3—C11	116.3 (2)	C36—C34—C32	119.2 (2)
C15—N3—Fe1	116.29 (15)	C36—C34—C35	117.16 (19)
C11—N3—Fe1	126.34 (16)	C32—C34—C35	123.08 (19)
C9—C10—C6	119.2 (2)	C25—C23—C22	118.5 (2)
C9—C10—H10	120.4	C25—C23—C24	118.8 (2)
C6—C10—H10	120.4	C22—C23—C24	122.7 (2)
N1—C5—C4	124.2 (2)	O6—C33—O5	124.2 (2)
N1—C5—H5A	117.9	O6—C33—C32	123.6 (2)
C4—C5—H5A	117.9	O5—C33—C32	112.2 (2)
C1—C2—C3	120.4 (2)	C22—C28—C27	122.2 (2)
C1—C2—H2	119.8	C22—C28—H28	118.9
C3—C2—H2	119.8	C27—C28—H28	118.9
C7—C6—C10	116.5 (2)	C31—C30—C29	120.0 (2)
C7—C6—C3	121.9 (2)	C31—C30—H30	120.0
C10—C6—C3	121.6 (2)	C29—C30—H30	120.0
N1—C1—C2	123.4 (2)	O4—C24—O3	124.5 (2)
N1—C1—H1	118.3	O4—C24—C23	122.5 (2)
C2—C1—H1	118.3	O3—C24—C23	113.0 (2)
C5—C4—C3	119.6 (2)	C31—C32—C34	118.6 (2)
C5—C4—H4	120.2	C31—C32—C33	118.0 (2)
C3—C4—H4	120.2	C34—C32—C33	123.4 (2)
N2—C9—C10	124.1 (2)	C30—C31—C32	121.6 (2)
N2—C9—H9	117.9	C30—C31—H31	119.2
C10—C9—H9	117.9	C32—C31—H31	119.2
C6—C7—C8	119.9 (3)	C21—O2—Fe1	93.32 (13)
C6—C7—H7	120.0	C21—O1—Fe1	85.40 (14)
C8—C7—H7	120.0	O7—C35—O8	124.6 (2)
N2—C8—C7	123.5 (3)	O7—C35—C34	117.7 (2)
N2—C8—H8	118.3	O8—C35—C34	117.57 (19)
C7—C8—H8	118.3	C35—O7—Fe1 ⁱⁱⁱ	144.35 (15)
C11—C12—C13	119.1 (2)	C35—O8—Fe1 ⁱ	128.26 (15)
C11—C12—H12	120.4		

Symmetry codes: (i) $-x+1, -y+2, -z+1$; (ii) $x, y, z+1$; (iii) $x, y, z-1$.

Hydrogen-bond geometry ($\text{\AA}, ^\circ$)

$D-H\cdots A$	$D-H$	$H\cdots A$	$D\cdots A$	$D-H\cdots A$
O5—H5 \cdots N2 ^{iv}	0.82	1.86	2.677 (2)	171
O3—H3 \cdots N4 ^v	0.82	1.81	2.598 (3)	162

Symmetry codes: (iv) $x-1, y, z-2$; (v) $x+1, y, z+1$.