As the Fourier projection showed some disturbing diffraction ripples round the bromine atom due to finite termination of the series, a second Fourier difference projection was prepared with the bromine contributions subtracted. This projection shows much better resolution of the carbon atoms. The structure is shown schematically in Fig. 1. The angle of tilt of the chains is  $\tau = 66^{\circ}$ . The subcell is nearly orthorhombic with  $a_s = 5.52$ ,  $b_s = 7.02$ ,  $c_s = 2.50$  Å.

The co-ordinates obtained from this projection, referring to all the atoms falling within one asymmetric unit (one-quarter unit cell) but belonging to parts of three separate molecules, are:

$\mathbf{Atom}$	x/a	z/c	Atom	x/a	z/c
$\mathbf{Br}$	0.256	0.0156	C <sub>6</sub>	0.7205	0.2165
N	0.161	0.0278	$C_7$	0.2911	0.2438
$C_1$	0.1968	0.0650	$C_8$	0.1129	0.2178
$\overline{C_2}$	0.4003	0.0860	C	0.1179	0.1800
$C_3$	0.3737	0.1258	$C_{10}$	0.9315	0.1550
$C_4$	0.5563	0.1520	$C_{11}^{10}$	0.9320	0.1163
$C_5$	0.5270	0.1902	$C_{12}^{11}$	0.7580	0.0900

The consideration of this projection shows that the  $NH_3^+$  groups lie about 0.5 Å out of the planes occupied by the halide ions. This agrees with a similar displacement

observed by King & Lipscomb (1950b) for the low-temperature form of *n*-propylammonium chloride.

It is to be noted that the particular crystalline form of the *n*-dodecylammonium chloride and the bromide are approximately isomorphous and have the C-N bond at roughly 90° to the 001 plane, which is near to the value for *n*-propylammonium chloride (space group  $C_{2h}^3-C2/m$ ). All the three structures, however, are representatives of three different space groups.

In order to obtain more complete information on the packing of the hydrocarbon chains, it will be necessary to prepare the other projections of the unit cell.

We wish to thank Professors J. Monteath Robertson and P. D. Ritchie for great interest in this investigation, and C. J. McCron for help in the evaluation of data for the hydrochloride.

### References

KING, M. V. & LIPSCOMB, W. N. (1950a). Acta Cryst. 3, 222.

KING, M. V. & LIPSCOMB, W. N. (1950b). Acta Cryst. 3, 227.

VAND, V. (1951). Acta Cryst. 4, 104.

WYCKOFF, R. W. G. (1930). Z. Krystallogr. 74, 25.

# Acta Cryst. (1953). 6, 741

# Neutron-diffraction study of the structure of the A-form of the rare earth sesquioxides. By W. C. KOEHLER\* and E. O. WOLLAN, Oak Ridge National Laboratory, Oak Ridge, Tennessee, U.S.A.

#### (Received 23 April 1953)

In the course of experiments on the paramagnetic

\* This work constitutes part of a dissertation submitted to the University of Tennessee, Knoxville, Tennessee, in partial fulfillment of the requirements for the degree of Doctor of Philosophy. scattering of neutrons by rare earth ions, the results of which are reported elsewhere (Koehler & Wollan, 1953), neutron-diffraction data from powdered samples of  $La_2O_3$ ,  $Pr_2O_3$  and  $Nd_2O_3$  of normal isotopic constitution and  $Nd_2O_3$  enriched in  $Nd^{142}$ ,  $Nd^{144}$  and  $Nd^{146}$  were obtained which provide direct evidence in confirmation

Table 1.	Values	of $j F ^2$ for	$La_2O_3$ -type	structures
----------	--------	-----------------	-----------------	------------

	Pauling model	Zachariasen model			
	$\begin{array}{cccccccccccccccccccccccccccccccccccc$	$\begin{array}{llllllllllllllllllllllllllllllllllll$			
Index	u = 0.25, v = 0.65	u = 0.25, v = 0.25			
001	0.0207	6.06			
100	$6f_M^2$	$6f_M^2 - 6.96f_M + 2.02$			
002	$8f_M^2 - 1.77f_M + 0.0982$	$8f_M^2 - 13.9f_M + 6.07$			
101	$36f_M^2 - 33 \cdot 8f_M + 18 \cdot 1$	$36f_{M}^{2} + 4.04$			
102	$12f_{M}^{2} + 18 \cdot 2f_{M} + 18 \cdot 2$	$12f_M^2 + 13.9f_M + 4.04$			
003	5.66	6.06			
110	$24f_M^2 + 41 \cdot 8f_M + 18 \cdot 2$	$24f_M^2 - 13.9f_M + 10.1$			
111	0.124	20.2			
103	$36f_M^2 + 12 \cdot 9f_M + 7 \cdot 37$	$36f_M^2 + 4.04$			
200	$6f_M^2$	$6f_M^2 + 6.96f_M + 2.02$			
112	$48f_M^2 - 10.6f_M + 0.589$	$48f_M^2 + 27 \cdot 8f_M + 20 \cdot 2$			
201	$36f_M^2 - 33 \cdot 8f_M + 18 \cdot 1$	$36f_M^2 + 4.04$			
004	$8f_M^2 - 2 \cdot 89f_M + 0 \cdot 257$	$8f_M^{-}+13\cdot 9f_M+6\cdot 06$			

	Nd246O3	Calc.	0.2	10	53	67	80	77	$87 \times 10^{-12}$
		Obs.	:	17	55	67	84	75	$f_{\rm Nd}^{146} = 0$ .
	40 <sub>3</sub>	Calc.	0-4	n	46	58	65	30	$28 \times 10^{-12}$
	Nd14	Obs.	.	4	48	57	66	31	$f_{\rm Nd}^{144} = 0.5$
e scale	$\mathrm{Nd}_{2}^{142}\mathrm{O}_{3}$	Calc.	0-3	16	59	84	110	84	$77 \times 10^{-12}$
n an absolute		Obs.	[ ]	17	58	80	112	80	$f_{\rm Nd}^{142} = 0$
s/min.) are o	Pr <sub>5</sub> O <sub>5</sub> Nd <sub>2</sub> O <sub>3</sub>	Calc.	<b>L</b> ·0	21	11	112	146	105	$72 \times 10^{-12}$
ies (neutron		Obs.		22	80	111	144	98	$f_{\rm NA} = 0.$
All intensit		Calc.	0-4	6.5	47	11	87	44	$4 \times 10^{-12}$
		Obs.	1	5	50	71	86	48	fe. = 0.4
	03	Calc.	1.0	36	123	164	213	177	< 10 <sup>-12</sup> cm.
	La2	Obs.	I	35	122	166	213	178	$f_{T_0} = 0.83$

for the accepted structure of the hexagonal form of the rare earth sesquioxides.

The La<sub>2</sub>O<sub>3</sub> structure was first investigated by Zachariasen (1926, 1929) and his proposed structure was subsequently criticized by Pauling (1928), who proposed an alternative model on the basis of packing and other physical considerations. More recently, Zachariasen (1949) has pointed out the similarity of the structure of the oxysulfides of La, Ce and Pu to that suggested by Pauling for the hexagonal sesquioxides.

Although Pauling's structure is now accepted for these compounds, the light atom positions have heretofore been determined only indirectly; it was therefore felt that the direct evidence provided by the neuton-scattering data would be of interest.

The atomic positions for the two structures are shown at the top of Table 1, in which are tabulated structure factors calculated for the two models. The oxygen scattering amplitude has been taken as  $0.580 \times 10^{-12}$  cm.; but, since the scattering amplitudes of the rare earth nuclides had not been previously measured, the structure factors are expressed as functions of the metal scattering amplitude.

The structure first proposed can be eliminated without a knowledge of the metal scattering amplitudes by inspection of the diffraction patterns. For example, the reflections (001) and (111) are nearly independent of the metal scattering amplitude, and their intensities are seen to vary markedly from the one model to the other. In the diffraction patterns of all the samples studied the (001) and (111) reflections were immeasurably small. whereas on Zachariasen's model these lines would be among the strongest in the pattern.

An attempt was made to evaluate the parameters of the structure from the absolute intensities observed in the  $La_2O_3$  pattern alone, in order to avoid any possible coherent magnetic scattering effects in the magnetic salts. Since the intensity of the (100) reflection depends only upon the magnitude of the lanthanum scattering amplitude, an approximate value of  $f_{La}$  was obtained from this reflection, and by successive approximation the following quantities were evaluated:  $f_{La} = 0.83 \pm 0.01 \times 10^{-12}$  cm.,  $\theta = 410^{\circ}$  K.,  $u = 0.245 \pm 0.005$ ,  $v = 0.645 \pm 0.005$ . A comparison of the observed and calculated intensities for La<sub>2</sub>O<sub>3</sub> and for the oxides of Pr and Nd, assuming the same parameters and characteristic temperature, is given in Table 2 together with the nuclear scattering amplitudes (Koehler & Wollan, 1953) upon which the calculated intensities are based. The agreement is quite satisfactory for the entire series of samples and this suggests that coherent magnetic effects, if any, contribute less than 5% to the intensities observed.

The cooperation of Dr F. H. Spedding, of the Ames Laboratory, and the Stable Isotopes Division of ORNL in making these samples available to us, and of Mr B. S. Borie and Mr R. M. Steele for X-ray analyses of the samples, is gratefully acknowledged.

## References

- KOEHLER, W. C. & WOLLAN, E. O. (1953). Phys. Rev. 90, 354.
- PAULING, L. (1928). Z. Krystallogr. 69, 415.
- ZACHARIASEN, W. H. (1926). Z. phys. Chem. 123, 134.
- ZACHARIASEN, W. H. (1929). Z. Krystallogr. 70, 187.
- ZACHARIASEN, W. H. (1949). Acta Cryst. 2, 60.